

78
ANCIENT MONUMENTS LABORATORY

REPORT

2561

SERIES/No

ENVIRONMENTAL

34/78

AUTHOR

Carole Keepax

4.7.78

TITLE

Wood identification, Castleacre Priory

ANCIENT MONUMENTS LABORATORY

MATERIAL WOOD

CASTLE ACRE PRIORY
 SITE: (DATE: 4/7/78)
 SHEET: 1

M No	X-Ray No	Photo No	Description and Report	Ref No
66546	Wooden bowl		Probably hazel (<u>Corylus avellana</u> L.)	K F176 C
66547			Oak (<u>Quercus</u> sp.) and elm (<u>Ulmus</u> sp.)	K F176 C
66548			Oak	F173
66549			Probably oak (preservation poor)	C F173
66550			Oak	C F172
66551			This heavily iron stained, granular material superficially resembles wood, but there is very little surviving structure. A few areas, however, display the apparent remains of very wide medullary rays. The material may therefore have been oak wood originally.	C F172
66552			Oak	C/SILT/(
"			Oak	" (
"			Oak	" (
66553			Oak. This is the only timber which is marginally large enough for dendrochronological study.	K/Next

Carole A. Keepax
 Carole A. Keepax