

ANCIENT MONUMENTS LABORATORY

REPORT

3773

SERIES/No	CONSULTANT
AUTHOR	Miss E Crowfoot Sept 1982
TITLE	Baynards Castle, 14th century dock deposit. Textiles. Tabulation for AML Report 1754

Poor quality original

1952

[illegible]

Cat.no.	Excavat.no.	Measurement	Fibre	Spin	Weave	Count	Colour	Borders	Finishing	Sewing	Remarks
TA/8 (con.)	3423/33	8.0 X 6.0	W	Z/S	tabby	10-13/2-13	pink-brown	-	?fulled	x	curved, ?other armhole, broken stitches both sides, other scraps
	3423/30	c.13.0 X 5.0	S	Z/U	tabby	est.32/28	pale brown	-	-	x	ragged, with two tiny scraps facing, stitched Z, 3ply silk
	3423/101	4.0 X 2.0, (4.5 X 1.5)	W	Z/S	tabby	11/10-12	pink-brown	-	?fulled	x	bias-cut, edges not turned under, ?parts circle, silk 3ply stitches from facing to raw edge; other scraps
TA/9	3424/9	c.14.0 X 9.0	W/W, S+	Z/S 3ply	tabby extended	9/10 4-5prs/6	dark brown/dark brown ?yellow	-	fulled	x	(Pl.) armhole fragment, two silk stripes paired warps, 9 cm apart; curved edge, facing out straight, r.st. edge, hemmed (p.
			S	Z/U	tabby	est.34/26	mauve-pink	-	-	x	facing out straight, r.st. edge, hemmed (p.
TA/10	3424/21	9.5 X 5.5	W	Z/S	2/1 twill	12/10	dark brown	-	?fulled	x	(Pl.) ?from collar, turned under edges, remains stitches facing held parallel lines r. st, tiny scraps (cf. TA/16)
			S	Z/U	tabby	est.34/26	?yellow	-	-	x	circle cut from neck (Pl. to enlarge child's dress; out straight facing, sewn 2 parallel rows r.st. dark brown 3ply silk
TA/11	3517/5	centre 3.0 diam. width 2.2 9 mm wide	W	Z/S	tabby	14/14	purple-red*	-	fulled	x	(Pl.) curved, neck or arm opening, faced bias cut silk hemmed, line r.st. centre of binding, edge corded silk (see TA/1, 2, 3)
			S	Z/U	tabby	est.42-44/36	mauve-pink	-	-	x	curved edge, traces sewing; one edge out, not turned in facing, selvedge turned under corded edge as in TA/1, 2, 3, 12.
TA/12	3517/35	6.0 X 1.6 1.0 wide	W	Z/S	2/1 twill	12/2	red-brown	-	fulled	x	(Pl.) curved, neck or arm opening, faced bias cut silk hemmed, line r.st. centre of binding, edge corded silk (see TA/1, 2, 3)
			S	Z/U	tabby	36/26	pale brown	-	-	x	curved edge, traces sewing; one edge out, not turned in facing, selvedge turned under corded edge as in TA/1, 2, 3, 12.
			S	U, 3ply	?tablet 4-hole	4 tablets	?yellow	-	-	x	curved edge, traces sewing; one edge out, not turned in facing, selvedge turned under corded edge as in TA/1, 2, 3, 12.
TA/13	3556/2	20.5 X 0.0 c.1.0 wide	W	Z/S	tabby	15-16/14-15	brown	-	?fulled	x	curved edge, traces sewing; one edge out, not turned in facing, selvedge turned under corded edge as in TA/1, 2, 3, 12.
			S	Z/U	tabby	est.34/40	?yellow	2.1(1.12-1.15prs)	-	x	curved edge, traces sewing; one edge out, not turned in facing, selvedge turned under corded edge as in TA/1, 2, 3, 12.
			S	U, 3ply	?tablet 4-hole	4 tablets	?yellow	-	-	x	curved edge, traces sewing; one edge out, not turned in facing, selvedge turned under corded edge as in TA/1, 2, 3, 12.
TA/14	3556/43	6.0 X 4.0 7 mm wide	W	Z/S	2/1 twill	15/10	brown	-	fulled	x	curved edge, traces sewing; one edge out, not turned in facing, selvedge turned under corded edge as in TA/1, 2, 3, 12.
			S	Z/U	tabby	36/?	pale brown	-	-	x	curved edge, traces sewing; one edge out, not turned in facing, selvedge turned under corded edge as in TA/1, 2, 3, 12.
TA/15	4085/1(a)	L.7.0	S	Z	?tablet,	3 tablets	?yellow	-	-	x	curved edge, traces sewing; one edge out, not turned in facing, selvedge turned under corded edge as in TA/1, 2, 3, 12.
			S	Z/U	tabby	7/6 on 3mm	?yellow	-	-	x	curved edge, traces sewing; one edge out, not turned in facing, selvedge turned under corded edge as in TA/1, 2, 3, 12.
TA/16	4088/4	c.13.0 X 12.0	S	Z/U	tabby	36/40-41	pale yellow	-	-	(x)	(Pl.) ? from front collar 3 edges turned under, lines from r.stitches, 2.5 mm apart, in pattern of TA/10

<u>Cat.no.</u>	<u>Excavat.no.</u>	<u>Measurement</u>	<u>Fibre</u>	<u>Spin</u>	<u>Weave</u>	<u>Count</u>	<u>Colour</u>	<u>Borders</u>	<u>Finishing</u>	<u>Sewing</u>	<u>Remarks</u>
TA/17	3423/33(a)	6.0 X 3.0	W	Z/S	tabby	10-11/9-11	pale brown	-	fulled	-	(Pl.) small leaf-shaped dagge from sleeve, tunic hem, or edge of hood shoulder cape; edges cut, no sign of sewing 6 fragments, one ?tied in bunch
	3423/32	9.0 X 3.5, 7.0 X 3.0, 4.0 X 3.0									
TA/18	3517/49	L. 33.0, c.22.0, width c.6.0	W+	Z/S	tabby	11/13	dark rich brown*	-	fulled	-	(Pl.) 2 long dagges from hem, sleeve or hood; long points (centre rib 3.0 wide) no sign sewing. On both, group 3 holes, ?sewing or pinning, jewel, metal ring or besant?
TA/19	3423/30	3.0 X 17.0	W	Z/S, Z	tabby	9/13 12 on 5mm	dark brown/dark, lt. brown	3 fringe	-	-	(Pl.) narrow band near end finer 7, 8 mm wide; fringe warp ends pairs, 3ply, added light threads twisted in remains warps plied 3, 3, and and then 10 (i.e. 30 warps) tied simple finger knot scraps, top edge turned over 7 fragments
TA/20	3423/88	6.5 X 4.0	W	Z/S	2/1 twill	12-14/12	pink-brown	3 fringe	fulled	-	(Pl.) ?part of collar, top edge folded, end squared, silk stitching; along top remains 10 bobbles, 6 mm apart, ? stinks, wound natural silk, 1 bobble brown W
	3556/23	5 X 2.3, 3 X 1.2									
	3556/51	4.7 X 7.5, 5 X 2.5,									
TA/21	3424/23	7.5 X 4.5	W	Z/S	2/1 twill	8/12	bright brown	-	fulled	-	(Pl.) fragment edge ? from collar, lined shiny W, turn; 5 buttons or bobbles, stumps & traces more, made of ? main weave, rounder, seen 40ply silk; ?main weave seen into bobbles along folded edge, continuous thread (p. Decorative lining ?showed in front.
TA/22	3517/4	6.5 X 2.0 c.6.5 X 1.6	W W+	Z/S S/Z	2/1 twill 2/2 twill	14/9-10 18/28	brown* red*/?white	- -	- -	x	

(See p.27, TA/429, TA/430)

TA Catalogue..

Cat.no.	Excavat.no.	Measurement	Fibre	Spin	Weave	Count	Colour	Markers	Finishing	Sewing	Remarks
TA/23	3517/95	3.0 X 10.0	W	Z/S	tabby	9/9	dark brown	B fringe	fulled	-	fringe, L.2.5 where best, groups 4 or more warps plyed S pairs then plyed Z together, ends fulled into solid lumps
TA/24	3656/9	2.0 X 14.0, 15.0 X 2.0	W	Z/S	tabby	12-13/9-10	brown	B fringe	fulled	-	2 fragments, one with remains fringe, warps 4 plyed S
TA/25	3423/19	21.0 X 3.0	W	Z/S	tabby extended tabby	11-15/10-13	brown/brown,* red-br,red-purple, lt.golden-brown		?fulled	-	strip, 2 bands 2.8 wide, 11.2 apart, over 2 warps, 4 red-br, red-purple c.16, light brown (decayed) 7 mm, red-pu., red-br.
	3423/63	17.0 X 4.0, 8 X 5.5, 5 X 5.5 4.5 X 5.0								(x)	6 fragments, largest folded 3 cm, gathered, stitches gone, ? top of skirt (Pl.)
	3423/103	14.0 X 6.0, 12.5 X 2.5								x	fragment, folded, stitchmarks;
	3656/76	8.5 X 1.3						3.1.2(3)		x	bias-cut, folded, stitch marks; and four others
TA/26	3423/21	2.4.0 X 3.0	W	Z/S	tabby	11-17/12-13	brown	-	fulled	x	selvedge strip; 2 other strips very fine thread; edge turned over, broken all stitches
TA/27	3424/16(b)	12.0 X 3.0	W	Z/S	tabby	12-14/10-13	light brown	-	fulled	(x)	cut rectangle, ? collar band, all edges turned under.
	3424/16(c)	12.0 X 2.0, 10.5 X 3.5								(x)	turned under long edge
TA/28	3424/17(a)	10.0 X 3.0	W	Z/S	2/1 twill	10, 11-13	mid brown	-	fulled	(x)	2 adjoining, edges turned; & strip. ? gusset, triangle, edges turned.
	3424/16	10.0 X 4.0								(x)	cut triangle left uneven.
TA/29	3424/31(b)	12.0 X 2.4, 9.5 X 8.0	W+	Z/S	2/1 twill	8-10/7-9	grey brown/ grey-br, red	3.1.2 (3)	fulled	-	+ turned under long side & point selvedge; red cords; other turn 2 sides meeting right angle.
	3424/31(a,d)	5.0 X 7.0, 8 X 7.5, 4.5 X 7								(x)	fragments; in all weft thread uneven, lumpy.
TA/30	3517/102	14 X 8.0	W	Z/S	2/1 twill	12-13/7-10	rich brown*	-	fulled	(x)	cut oval, stitch marks, scraps perhaps from collar.
	3424/31(c)	13 X 10, 4.5 X 7								(x)	other fragments; 1 fine, 3 turned coarse
TA/31	3517/107	5.0 X 12.0	W	Z/S	2/1 twill	11/11-12	rich brown	-	fulled	(x)	triangle turned over, stitch-
	3517/32	11.5 X 4.8, 14.0 X 1.5	W	Z/S	2/1 twill	11/11-12	rich brown	-	fulled	(x)	marks, & long strip
TA/32	3424/39	24.0 X 16.5	W+	Z/Z	2/2 twill	8/7	dark brown	3.1	-	(x)	? top edge & selvedge turned under, stitch holes; slit at bottom edge, sides turned back ? for core (p.
TA/33	3424/43(b)	15.5 X 3.0	W	Z/S	tabby	12/13-14	dark brown	-	fulled	x	band of sleeve, - - - - - silk etc.

<u>Cat.no.</u>	<u>Excavat.no.</u>	<u>Measurement</u>	<u>Fibre</u>	<u>Spin</u>	<u>Weave</u>	<u>Count</u>	<u>Colour</u>	<u>Borders</u>	<u>Finishing</u>	<u>Sewing</u>	<u>Remarks</u>
TA/34	{ 3424/44 3656/26 3656/72	6.0 X 4.5 3.5 X 7.5 13.0 X 7.0	W	Z/S	tabby	9-11/10-11	red-brown	-	-	-	pinked edges from seam (x) edge turned under, stitch marks (x) corner turned, stitch marks, 7 other fragments
TA/35	{ 3517/87 3424/46	12.5 X 5.5 5.0 X 3.0 11.5 X 7.0, 8.5 X 7.5, 9 X 5	W+	Z/S	tabby	9-11/8-11	dark brown*	-	-	(x)	top edge turned over, point for gore insertion, stitch marks; triangle stitch marks, ?gore fragments; and small scraps
TA/36	3424/54	9.0 X 5.0 10.0 X 8.0	W	Z/S	tabby	17/12	dark brown	-	fulled	x	tiny fragment slanting seam, still held 1 stitch Sply silk
TA/37	3424/58	6.0 X 3.5	W	Z/S	tabby	12-13/11	brown	-	fulled	x	(torn in two) edge curved, turned under, held r.st. Sply yellow silk; other end slit?for gore
TA/38	3424/60(d)	11.5 X 9.0	W	Z/S	tabby	11/9	pink-brown	-	-	-	wedge-shaped, torn ends, part skirt gore, one side straight of weave, other bias-cut (p. edges turned under.
TA/39	{ 3517/127 3517/16	10.0 X 3.2, 5.5 X 2.3, 7 X 1.5 6.0 X 0.6	W	Z/S	2/1 twill	11-12/8-9	rich brown	-	fulled	(x)	all one edge turned under, stitch marks 3 mm apart bias-cut strip
TA/40	3517/17	3.8 X 1.4	W	Z/S	tabby	10-11/10-11	dark brown	-	fulled	(x)	triangle ?point gore, pinked edges, stitch-holes 3-4mm from edge
TA/41	{ 3517/105 3517/10	4.0 X 1.2 10 X 3.2, 10 X 1.3	W	Z/S	tabby	9-11/9-10	red-brown	-	?shaped	x	cut edge, broken yellow silk stitches. 2 torn fragments
TA/42	{ 3517/59 3517/56	10.0 X 4.0 3.5 X 1.4, 3.3 X 1.8	W	Z/S	tabby	17-13/9-12	rich brown*	-	-	(x)	piece with slit 5.5 long, edges folded & tacked (stitch-holes); top long edge turned under fragments & scrap
TA/43	3517/54	6.0 X 1.0	W	Z/S	tabby	15/18	crimson	-	?fulled	(x)	bias-cut, edge turned, stitch marks
TA/44	{ 3517/65 3517/57 3517/164	10.5 X 9.0 16.0 X 2.5 12.0 X 4.0 8.5 X 9.0 2.5 X 9.0	W	Z/S	2/1 twill	13-14/9-12	dark brown	-	fulled	(x)	top edge turned over, slit 7 L. pinked edges, stitch-holes ? part of old sleeve; triangle cut, ?from collar, 3 sides stitches cut fragments, turned under edges.
TA/45	{ 3517/76 3517/81	17.0 X 10.0 9.0 X 5.5	W	Z/S	tabby	10/12-13	brown	-	fulled	x	2 pieces joined (Fl.) seam middle, sewn double Espun W, ends turned under top & one other edge; area cut for re-use 2 pieces seamed as above, curved edges turned under.
A/46	3517/77	6.7.5 X 3.5	W	Z/S	tabby	10/6-7	mid brown	-	fulled	(x)	edges pinked, ...

<u>Cat.no.</u>	<u>Excavat.no.</u>	<u>Measurement</u>	<u>Fibre</u>	<u>Spin</u>	<u>Weave</u>	<u>Co nt</u>	<u>Colour</u>	<u>Borders</u>	<u>Finishing</u>	<u>Sewing</u>	<u>Remarks</u>
TA/47	{ 3517/38 3517/123	4.5 X 1.7, 7.0 X 5.0 3.7 X 4.5	W	Z/S	tabby	13-11/10-11	brown	-	fulled	(x)	2, edges turned under, marks stitches curved, edge turned under, stripes due to wear (?gathers) one side
TA/48	{ 3517/98 3517/159 3517/163	17.0 X 3.5 4.5 X 1.4 17.0 X 1.3	W+	Z/Z	2/1 twill	14-16/12-13	dark brown	C.1.1(3? or?A. (fig.1.h)	?fulled	(x)	selvedge turned under, stitch- marks 8 mm from edge, second 1 line 5.5, ?tuck; selvedge 2 wefts, or ?A border (p. selvedge strip sewn in seam? selvedge; both edges folded
TA/49	{ 3517/100 3517/150 3517/169	12.0 X 27.0, .5X7, 10 X 6.0 3 X 4, 1.8 X 2.0 2.5 X 9.0	W	Z/S	2/1 twill	10/8-10	mid brown	-	?fulled	(x)	diagonal fold across corner, stitch marks; fragments worn fragments
TA/50	{ 3517/128 3556/36 3556/38	10.5 X 1.0 12.0 X 1.0 2.5 X 10.0	W	1/S	2/1 twill	13-15/8-11	rich pink-brown	-	fulled	(x)	edges, folded under, fold with stitch-holes in middle, bias facing or neckband. bias-cut strip triangle, cut edges, one turned cut strip
TA/51	3517/131	1.5 X 2.5	W	Z/S	2/1 twill	15/12	mid brown	-	fulled	(x)	cut edges, 1 torn; bunched centre as if flat or sewn.
TA/52	3517/152	11.0 X 7.5	W	Z/S	2/1 twill	13-14/11-12	black, uneven	-	-	(x)	stitch holes on 2 meeting sides
TA/53	3556/1	4.0 X 12.0	W	Z/S	2/1 twill	14-15/13	black	-	fulled	(x)	edges, edge turned up from silk blast.
TA/54	3556/2	11.0 X 4.0	W	Z/S	tabby	11/11-12	black	-	fulled	(x)	part skirt gore, one side bias, one straight, point turned under stitch marks. Cf. TA/38.
TA/55	3556/13	13.0 X 19.0	W+	Z/S	tabby	11/7-8	dark red*	-	?fulled	-	curved edge turned under, ?arm- hole jacket or gown.
TA/56	3556/16	1.5 X 6.0	W	Z/S	tabby	c.12/12	brown	-	-	x	and tiny scrap, both edge turned under, tufts yellow Sply silk, ?sleeve end
TA/57	3556/70	7.0 X 9.5	W	Z/S	tabby	11/10	dark brown	-	?fulled	(x)	cut edges, traces tuck (warp way) widening end, stitches both sides.
TA/58	4710/6	15.5 X 14.0 14.0 X 8.0 8.0 X 6.5 4 X 6, 8 X 12, 5 X 11	W+	Z/Z	2/2 twill	22-24/20	very dark brown*	-	-	(x)	sloping edge cut, turned double, stitch marks hemming; top turned under double, sloping, corner turned under to meet; bias-cut, turned under single; ? fragments; all can be assembled 1.42, on bias, on 1st corner. Pl.

Cat.no.	Excavat.no.	Measurement	Fibre	Spin	Weave	Count	Colour	Borders	Finishing	Sewing	Remarks
TA/59	3515.5673	L.6.4,width 1.2-1.25	S+	Z, Sply/Z, Sply	4-hole tablet, (132-140 wps) double- faced pattern	33-35 twists /25-26 wits	pale brown*	-	-	-	(Pl. ,p.) edge twists gone pattern diamonds, filled 9 small diamonds; ?textural, or decay of one thread due to dye?
TA/60	3695	Ls.15.0,9.0, width 1.0	S	Sply/Sply	tablet, 64/c.46 4-hole edge, 2-hole centre		pale pink- brown *	2 3 twists, 1.25 wide	-	x	(Pl.) braid, sewn Sply silk to false hair plait(+), two pieces; centre regular tabby effect, (p.); intervals c.1.0, groups holes from ?metal or jewels, ornaments cut off when discarded.
TA/61	3423/11 3423/41	23.0 X 1.5-1.7 (a) L.23.0 X 3-6 mm	W	Z/S	tabby	11/8-9	brown	-	fulled	-	3 strips, knotted 2 reef knots 2 strips tied double knot; one selvedge, cf. TA/21a, p.
		(c) L.22, X 1.2-0.9 (d) L.8, 1.2-1.3	W	Z/S	tabby	11-12/9-10	brown	-	-	-	(c,d) 2 strips, (c) 2 knots, (d) 1; both a strip from tabby, c and a twill selvedge strip
TA/62	3317/31	19.0 X 1.0	Z	Z/S	2/1 twill	12/11	dark brown	1.1 (fig. 1.4)	fulled	-	2 selvedge strips tied reef knot
<u>2. Silk weaves</u>											
TA/63	4709/10	12.0 X 7.0	S/S ?	U/U	compound twill, 1/2	12-13/ binder, c.24 prs main	dark gold/ pale gold, ?moss	-	-	p	(Pl. ,p.) wider weaves fine, pattern leaf and fruit scroll ? pattern not gone in areas leave loose, ?metal covered flex (metal traces on back).
TA/64	4709/11	14.5 X 5.5	S	U/U Z	compound twill, 1/2	18 binder/34-36 main	ite, white, or yellow pink, ?pale green	-	-	-	(Pl. ,p.) weave as in 63, but main bands single; leaf scroll pattern?
TA/65	4709/12	14.0 X 6.0, 3.0 X 2.4	S+	U/U	hemask, twill base, tabby pattern	28/12-14	orange-red* (dark brown)	-	-	x	(Pl. ,p.) smaller fragment edges turned under, fastened r.st., sply brown silk; same turned on larger piece, but hem pulled out; pattern damaged, ?leaf scroll
TA/66	4088/1	11.0 X 11.0	S	Z/U	tabby	40-46/29-34	dark gold*	-	-	-	actual, weave pulled
TA/67	4088/2	c.6.0 X 3.0	S	Z/U	tabby	31-42/25-26	dark gold	-	-	-	very similar to TA/66, darker
TA/68	4088/3	17.0 X 35.0	S	Z/U	tabby	34/21-27	pale brown ?white	-	-	-	left thread variable, giving striped effect

Cat.no.	Excavation no.	Measurement	Fibre	Spin	Weave	Count	Colour	Borders	Finishing	Sewing	Remarks
TA/69	4909/7	7.0 X 15.5	S	Z/U	tabby	38/30	pale brown ?white	C.1.1(6)	-	-	Z spin in warp slight; selvedge 8 warps 2 mm after edge cord
TA/70	4909/8	8.9 X 26.0	S	Z/U	tabby	38/41	dark gold	C.1.1(4)	-	-	very similar to TA/70 but darker, selvedge 4 single warps 1 mm after cord.
TA/71	4909/9	9.0 X 15.2	S	Z/U	tabby	38/40	dark gold*	-	-	(x)	turned under on three sides, traces rather coarse sewing on all four.
<u>3. Wools</u>											
TA/72	{ 4710/7 3656/107	{ 9.5 X 4.5 21.5 X 3.5	W+	Z/Z	6-shed waved twill, band extended tabby (over 3 warps)	27/37- 38	pink-red/?white pink-red, purple*	-	-	-	(Pl. ,p.) fragments cut bias, shiny wool; parts band 1.0 wide, - tabby 6 white, 6 purple, twill 20 pink-red, tabby 6 white, 6 purple (fig.
TA/73	3424/27	8.5 X 7.5	W+	Z/Z	3/3 diagonal twill	21/33	rich brown*	-	-	-	(fig. 2.b, Pl.) very fine & regular yarns, silky W
TA/74	400/5	2.5 X 3.0	W+	Z/Z	3/3 diagonal twill	25/26	pink-brown*	-	-	(x)	triangular, bias-cut, ?warp finer & harder; long edge turned under, stitch marks
TA/75	400/6	5.0 X 5.0	W+	Z/Z	3/3 diagonal twill	24-26/26	red-brown*	-	-	(*)	diamond shaped, folded, one end stitch marks; possibly part of TA/74, but colour & preservation better
TA/76	3423/2	1.0 X 5.0, 12.0 X 4, 6 X 2, 4 X 4, 3 X 3	W+	Z/Z	2/2 twill	12/14	mid brown	-	-	-	spin uneven, weave regular 2/2 diagonal, (fig.)
TA/77	3423/4	2.5 X 2.2	W+	Z/Z	2/2 twill	16/17	grey brown	-	-	-	very solid weave
TA/78	3424/33	8.6 X 5.0	W	Z/Z	2/2 twill	14-15/18	dark brown	-	-	-	ragged
TA/79	3424/35	13.5 X 2.0	W	Z/Z	2/2 twill	8/6	very dark brown	-	?fulled	-	coarse threads
TA/80	3424/36	11.0 X 2.2	W+	Z/Z	2/2 twill	16-17/14	red*	C.1(1pr*)	-	-	strip
TA/81	3424/38	8.7 X 4.0	W+	Z/Z	2/2 twill	9/9	dark brown	-	-	-	triangle, folded long edge
TA/82	3517/6	13.0 X 6.0	W	Z/Z	2/2 twill	14/13-14	brown	-	-	-	?warp even, weft uneven, giving striped appearance
TA/83	3517/7	5.3 X 4.0	W+	Z/Z	2/2 twill	10/7-8	dark brown	-	fulled	-	cut edges, ?tailor's waste
TA/84	3517/97	7.2 X 2.5	W+	Z/Z	2/2 twill	12/12	near black	-	?fulled	-	even spinning
TA/85	3517/124	10.0 X 0.9	W	Z/Z	2/2 twill	12/12-13	rich brown	C.1.1(4)	-	-	selvedge strip
TA/86	3573/3	13.5 X 8.0, 17.9 X 11.5	W+	Z/Z	2/2 twill	16-18/14-16	dark brown	-	-	-	rectangle, adjoining sides turn under; one side turned under; uneven spin and weave
TA/87	3656/21	28.0 X 1.5	W+	Z/Z	2/2 twill	18/14	brown	-	-	-	cut strip
TA/88	3656/79	7.0 X 5.5, 5.0 X 5, 3.0 X 5.5	W	Z/Z	2/2 twill	16/14-16	light brown	-	-	-	square, slightly folded

<u>Cat.n.</u>	<u>Excavst.no.</u>	<u>Measurement</u>	<u>Fibre</u>	<u>Spin</u>	<u>Weave</u>	<u>Count</u>	<u>Colour</u>	<u>Borders</u>	<u>Finishing</u>	<u>Sewing</u>	<u>Remarks</u>
TA/89	3634/30	3.5 X 4.5	W+	Z/Z	2/2 twill	11/10	bright brown	-	-	-	surface slightly shiny
TA/90	3636/21	2.5 X 6.5	W	Z/Z	2/2 twill	11/11	yellow brown	-	-	-	triangular, yarns uneven
TA/91	3636/32	17 X 12, 13.0 X 9, 6 X 2.5, 8.0 X 4	W+	Z/Z	2/2 twill	13-14/14	dark purple- brown	-	-	-	one folded on curve; two tiny scraps
TA/92	3636/34	3.5 X 2.0	W+	Z/Z	2/2 twill	16/16	very dark brown	-	fulled	-	with TA/83 only Z/Z twills fulled
TA/93	4710/2	6.0 X 1.0	W+	Z/Z	2/2 twill	28/26	light brown	-	-	-	fine regular spin and weave
TA/94	4710/3	6.0 X 3.0	W+	Z/Z	2/2 twill	16/16	rich brown	-	-	-	very even spin and weave
TA/95	4710/5	6.5 X 3.3	W+	Z/Z	2/2 twill	24/24	light brown*	0.1(1)	-	x	warp very fine, weave open, 2, 3 ply natural silk thread run along near selvedge
TA/96	4809/1	3.2 X 3.4, 2.7 X 3, 2.5 X 2	W+	Z/Z	2/2 twill	24/28	reddish*	-	napped	-	yarns fine, well spun; raised fibres red-mauve, ?dyeing done after napping, or one system only dyed
TA/97	4809/3	19.0 X 1.7	W+	Z/Z	2/2 twill	26/29	pink-brown*	-	-	-	merino-range wool, shiny
TA/98	4809/1	5.0 X 2.4, 7.0 X 1.8	W+	Z/Z	2/2 twill	20/10	dark brown	0.1	-	-	2 selvedge strips, end turned under on longest, fine shiny wool
TA/99	3423/6	7.5 X 5.0	W	Z/S	2/2 twill	12/12	red purple-brown	-	-	-	colour uneven; weaving mistake or ?damaged threads
TA/100	3423/9	7.5 X 4.5	W	Z/S	2/2 twill	10/8	rich brown	-	-	-	one small scrap
TA/101	3417/2	6.0 X 7.0	W+	Z/S	2/2 twill	10-11, 7-8	dark brown, light brown	-	-	-	stripes in ?warp, 1.3 light, 4 warps dark, 4 light, 6 dark, 4 light, 6 dark, rest (0.8) light ?admal (p.)
TA/102	3517/10	5.5 X 5.5	W	Z/S	2/2 twill	10/7	dark brown/light brown	-	-	-	very similar to TA/101, warp hard, weft soft, deteriorated
TA/103	3417/13	5.7 X 4.3	W	Z/S	2/2 twill	9/8	dark brown	-	fulled	-	triangle, cut, tailor's waste
TA/104	3517/8	6.25 X 2.5	W	S/S	2/2 twill	10-11/9	light brown	-	-	-	two scraps
TA/105	3517/12	35.0 X 1.8	W	S/S	2/2 twill	6.10/10	light brown	-	fulled	-	?new, tailor's waste, long strip ending in point, yarns quite similar, solid fulling
TA/106	342-/37(b)	3.0 X 2.0, 3.5 X 6.0	W	Z/S	2/1 twill	10/8	light brown, /light brown red red	-	fulled	-	(fig.3.a.p.) warp 1 light brown(?white), 1 red; weft 1 red, 3 light brown; very uneven yarn, i.e. warp face front
TA/107	3517/121	11.0 X 6.0	W+	Z/S	2/1 twill	14/9	pink-red, /pink-red, light brown lt.brown	-	?fulled	-	warp, 6 pink, 6 light brown ? white, weft 4 pink, 4 light brown
TA/108	345/52	6.0 X 14.0	W	Z/S	2/1 twill	15/10-11	red, light/red, light brown brown	-	fulled	-	(fig.3.c) cut triangle; warp 2 red, 6 light brown, weft 2 red, 4 light brown

Cat.no.	Exposet.no.	Measurement	Fibre	Spin	Weave	Count	Colour	Borders	Finishing	Sewing	Remarks
TA/109	3317/120	1.3 X 6.5	W	Z,S/Z,S	2/1 twill	12-13/12	dark brown/dark brown, light brown light brown	-	-	-	cut edges; ?warp, Z fine, dark S light coarser, 6Z, 1S, 3Z, 1S; ?weft, 2 coarse dark, S, 2 finer light Z (fig.3.)
TA/110	3656/53	2.7 X 14.0, 3.0 X 6.5	W	Z/Z,S	2/1 twill	12-13/12-13	dark brown	-	-	-	?warp all fine, ?weft alternate 3 fine Z, 2 coarse S, all now same colour (fig.3.c)
TA/111	{ 3456/38 3456/35	3.0 X 2.5 5.0 X 4.0	W+	Z/Z, Sply, S	2/1 twill	15-16/5-6 16-18/5-6	light brown/bright, dark brown	-	-	-	?warp fine, overspun; ?weft alternate coarse dark S and bright brown plyed (fig.3.f)
TA/112	3656/53	4.0 X 7.0	W	Z/S,Z	2/1 twill	11/12	dark brown	-	?fulled	-	shiny, ?warp Z, ?weft 2S, 1Z alternate, all now same colour
TA/113	3424/29	24.0 X 2.0	W	Z/S	2/1 twill	11/8	light brown/light pink-red brown	C.1(2)	?fulled	-	strip, selvedge turned under pink-red pairs (fig.1.a)
TA/114	3656/106	2.0 X 3.4, 6.0 X 1.5, 4.0 X 2.5	W+	Z/S	2/1 twill	10/7-8	light brown/light	C.1 (fig.1.b)	-	-	three strips; selvedge on all, 3 prs. light brown, 1 blue warp, 1 blue, 1 brown es pair, 1 blue single; loose weave
TA/115	{ 3423/5 3423/49 3423/51	4.0 X 2.0 5.5 X 2.5 2.5 X 3.5	W	Z/S	2/1 twill	7-8/5-6	mid brown	-	?fulled	-	both yarns coarse, weft coarser and more uneven cut edges
TA/116	{ 3423/7 3423/52	15 X 9, 2.5 X 6.5, 7 X 5, 4.5 X 3, 8 X 2.5, 4 X 2.5 2.0 X 6.0	W	Z/S	2/1 twill	12-13/9-11 11/9	red-brown*	-	?fulled	-	six scraps, weft thread fine more regular
TA/117	{ 3423/34 3423/8	6.10.0 X 5.0 12.0 X 2.0	W	Z/S	2/1 twill	13/12 13/14	mid brown	C.1(?)	fulled	-	better preserved selvedge (fig.1.d, damaged; warp fine, weft uneven
TA/118	{ 3423/32 3423/40	4.0 X 22.0 3.5 X 6.0	W	Z/S	2/1 twill	13-14/7-8	mid brown	-	-	-	warp fine, regular, weft uneven, lumpy
TA/119	{ 3423/35 3423/39 3656/49	3.0 X 5.0 3 X 5, 4.0 X 6.5 10 X 31, 10.4 X 8.5, 4.0 X 10.0	W	Z/S	2/1 twill	11-15/8-11	mid brown	-	fulled	-	yarns variable; 1 edge turn under; curved 1 out triangular, 2 curved edges turned under, 1 strip and smaller fragments
TA/120	{ 3423/60 3423/36 3517/170	5.0 X 4.5 1.5 X 3.0 3.5 X 4.5	W	Z/S	2/1 twill	12-14/10	light brown	-	?fulled	-	S yarn overspun, worn
TA/121	{ 3423/37 3423/55	5.0 X 2.0 20.0 X 10.5	W+	Z/S	2/1 twill	10-12/5-6	mid brown	-	fulled	-	color uneven, coarse yarns

Cat.no.	Excavat.no.	Measurement	Fibre	Spin	weave	Count	Colour	Borders	Finishing	Sewing	Remarks
TA/122	{ 3423/38 3423/97 3424/30 3424/34	c.2.3 X 1.5 5.5 X 4.0 c.11.0 X 5.5 c.8.5 X 4.0	W	Z/S	2/1 twill	12-13/10-13	light brown (?white)	-	fulled	-	S thread uneven
TA/123	{ 3423/41 3424/47 3424/48	3.0 X 8.0 1.5 X 6.5 c.9.0 X 2.0	W	Z/S	2/1 twill	12-15/7-8	dark brown* (blue)	-	?fulled	-	colour variable, worn one side, S yarn uneven; cut edges, 1 wedge, 1 bias-cut
TA/124	{ 3423/42 3424/13 3556/20	c.1.5 X 21.0 5.0 X 4.5 2 X 8, 1.8 X 6.0	W	Z/S	2/1 twill	12-15/8-10	dark brown	-	fulled	-	warp fine, weft soft, even weave; long strip cut on curve, one other cut edges
TA/125	3423/43	c.2.5 X 3.5	W	Z/S	2/1 twill	11-12/6-7	brown	-	fulled	-	weft coarse
TA/126	3423/44	c.6.0 X 3.0	W	Z/S	2/1 twill	8/6	dark brown	-	-	-	both yarns alike, loose weave
TA/127	3423/46	3.0 X 6.5	W	Z/S	2/1 twill	12-13/8	light grey brown	-	fulled	-	weft coarse, cut triangle
TA/128	3423/49	7.5 X 12.5	W	Z/S	2/1 twill	12-14/12	mid brown	-	fulled	-	cut in half circle
TA/129	3423/53	2.5 X 2.5	W	Z/S	2/1 twill	14-15/13-14	red-purple	-	fulled	-	fine, regular, yarns alike
TA/130	3423/56	c.7.0 X 3.5	W	Z/S	2/1 twill	11/10	mid brown	-	-	-	both yarns alike
TA/131	3423/87(b)	c.14.0 X 3.5	W	Z/S	2/1 twill	16/14-15	brown	-	fulled	-	cut triangle, close weave
TA/132	{ 3423/96 3517/108	7.0 X 1.7 c.3.0 X 2.5	W	Z/S	2/1 twill	14-16/10	light pink-brown	-	fulled	-	cut triangle deteriorated
TA/133	3424/10	6.0 X 0.6	W+	Z/S S, Zply	2/1 twill	? /8	light brown (?white)	0.1(9)	-	-	selvage strip, pulled under by wefts, 2 edge warps S, Zply, then 7 prs(fig.1.c) no main weave preserved
TA/134	{ 3424/12 3517/167 3517/101	21.0 X 3.5 7 X 2.5, 5 X 2.5, 3.5 X 2.0 c.2.5 X 23.0	W	Z/S	2/1 twill	14/8-9 9-10/8-9 10/7-8	dark brown*	-	-	-	warp fine, weft uneven, lumpy threads looped back into picks, counts irregular
TA/135	3424/14(b)	13.0 X 4.5, 6.0 X 5.0	W	Z/S	2/1 twill	15/12	brown*	-	?fulled	-	ragged, diagonals Z cut, ?gusset
TA/136	3424/14(c)	6.5 X 10.0	W	Z/S	2/1 twill	15/10-11	brown	-	?fulled	-	worn, very like TA/135, but diagonals S - i.e. if same must have reverses
TA/137	3424/14(d)	10.0 X 12.0	W	Z/S	2/1 twill	11/10	light brown(?white)-	-	?fulled	-	ragged
TA/138	3424/15	19.0 X 3.2	W	Z/S	2/1 twill	14/15	brown	-	?fulled	-	cut strip, even spin, weave
TA/139	3424/16(a)	7.7 X 8.0	W+	Z/S	2/1 twill	12/8-9	light brown	-	fulled	-	damaged fibres
TA/140	3424/17(b)	6.5 X 6, 5.5 X 5	W	Z/S	2/1 twill	17/11	grey brown	-	?fulled	-	cut edges
TA/141	3424/19	7.0 X 3.5	W+	Z/S	2/1 twill	12-13/11	black(?blue)	-	fulled	-	bias-cut, even spin, weave
TA/142	3424/20	7.5 X 2.3	W	Z/S	2/1 twill	10/11	purple-brown*	-	-	-	even spin, weave, cut edges, new fabric
TA/143	3424/22	39.0 X 9.0	W	Z/S	2/1 twill	11-12/7-9	red-purple*	-	-	-	2 thread even, S irregular
TA/144	3424/24	2.0 X 12.5	W	Z/S	2/1 twill	12/12	brown	-	-	-	S thread uneven
TA/145	3424/26	c.4.2 X 5.5	W	Z/S	2/1 twill	9/7-8	red-purple*	-	?fulled	-	yarns, weave even; 2 small scrap

Cat.no.	Excavt.no.	Measurement	Fibre	Spin	Weave	Count	Colour	Borders	Finishing	Sewing	Remarks
TA/146	{ 3517/145 3424/37(a) 3656/17	4.3 X 1.2 14.0 X 2.0 3.7 X 5.7	W	Z/S	2/1 twill	12-14/12 12/9-10	red-brown*	-	?fulled	(x)	from seam, stitch marks in fold, 0.5 apart
TA/147	3424/40	11.5 X 2.5	W	Z/S	2/1 twill	13/9	brown	-	fulled	-	cut strip, curved edges
TA/148	3424/41(a)	c.6.0 X 5.0	W	Z/S	2/1 twill	11/10	light brown	-	fulled	(x)	triangle, sewing holes along one edge
TA/149	3424/42(b)	c.3.0 X 5.0	W	Z/S	2/1 twill	12/9-10	black	-	-	-	very uneven S thread
TA/150	3424/50(b)	11.0 X 7.5	W	Z/S	2/1 twill	9/9	rich brown	-	fulled	-	triangle
TA/151	3424/53(a)	c.8.0 X 9.0	W	Z/S	2/1 twill	13/10-11	rich mid brown	-	fulled	-	
TA/152	{ 3424/53(b) 3424/53(c)	c.11.0 X 11.0 c.16.0 X 4.5	W	Z/S	2/1 twill	11-13/10-11	dark brown	-	-	-	?matted by wear
TA/153	{ 3424/57(a) 3656/62	10.0 X 3.0 c.6.5 X 4.5	W	Z/S	2/1 twill	11-14/10-12 10/9	light brown	-	fulled	-	weft thread coarse, counts variable; 4 more scraps
TA/154	{ 3424/59(a) 3424/60(a)	29.0 X 2.8 10.0 X 3.0	W	Z/S	2/1 twill	15/14 12/11	light grey brown	-	fulled	-	and strip, very similar strip turned under, weave variable
TA/155	3424/60(b)	30.0 X 2.5, 8.5 X 5.0	W	Z/S	2/1 twill	12/10-11	brown*	-	fulled	-	strip turned under along edge; three other scraps
TA/156	3517/15	10.0 X 1.0	W	Z/S	2/1 twill	16/9-10	grey brown	0.1(?)	?fulled	-	tern selvage strip, 24 prs (damaged); weft yarn uneven
TA/157	3517/21	11 X 0.7, 6 X 0.6, W+ 2.7 X 13.0	W+	Z/S	2/1 twill	16/8-9	dark brown	-	fulled	-	strips, ?tailor's waste, cut long strip with rounded piece attached
TA/158	3517/42	5.5 X 1.3	W	Z/S	2/1 twill	8/11	brown	0.1(?)	-	-	strip selvage, heavy cords of 4 warps each, pulled into tube by wefts; warps paired in rest remaining
TA/159	3517/73	3.5 X 4, 4.5 X 6, W 4 X 3, 3 X 2.5 X 3, 3.0 X 2.5	W	Z/S	2/1 twill	13/9	grey brown	-	-	-	re s, loose weave, pigmented fibres clear
TA/160	3517/75	8.0 X 0.7	W	Z/S	2/1 twill	est. 14/9	grey brown	0.1(fig.1.3)	fulled	-	edge cord 4 warps, followed by 2 pairs, 2 wefts used
TA/161	{ 3517/158 3517/96	4.0 X 3.5 8.0 X 4.5	W	Z/S	2/1 twill	13/8-9	light brown	-	?fulled	-	curved edge turned under
TA/162	3517/99	8.5 X 3.5	W	Z/S	2/1 twill	13/11	mid brown	0.1(5)	fulled	-	edge worn into curve; selvage 3 prs, folded over
TA/163	3517/103	c.7.0 X 11.0	W+	Z/S	2/1 twill	8-9/5	dark brown+*	-	fulled	-	coarse yarns
TA/164	3517/104	14.0 X 6.5	W+	Z/S	2/1 twill	9/8	mid brown	0.1(fig.1.3)	-	-	long edge turned under
TA/165	3517/105	2.5 X 14.0	W	Z/S	2/1 twill	10/10-11	dark brown	-	fulled	-	visible black fibres
TA/166	3517/109	16.5 X 2.3	W	Z/S	2/1 twill	14/11	dark brown	-	fulled	-	cut edges, one turned under
TA/167	3517/125	15.0 X 2.0	W	Z/S	2/1 twill	9/8	dark brown	-	?fulled	-	both yarns even, weft coarse

<u>Cat.no.</u>	<u>Excavat.no.</u>	<u>Measurement</u>	<u>Fibre</u>	<u>Spin</u>	<u>Weave</u>	<u>Count</u>	<u>Colour</u>	<u>Borders</u>	<u>Finishing</u>	<u>Sewing</u>	<u>Remarks</u>
TA/168	3517/126	8.0 X 2.5, 4.0 X 2.5	W	Z/S	2/1 twill	9/7	brown	C.(fig.1.b)	-	-	coarse yarns; selvedge 4-5 prs in one place 2 picks seem to miss edge warp cord
TA/169	{ 3517/129 3517/144 3517/154	9.0 X 1.6 6.5 X 1.5 c.4.0 X 5.5	W	Z/S	2/1 twill	14/11 12-13/10 12/9	dark brown*	-	fulled	-	cut edges, variable weave
TA/170	3517/130	12.0 X 1.2	W	Z/S	2/1 twill	12/11	rich brown	-	fulled	-	cut strip
TA/171	3517/132	8 X 8, 6.5 X 8	W	Z/S	2/1 twill	10-11/7-8	brown	-	?fulled	-	coarse uneven weft
TA/172	3517/133	4.5 X 7.0	W	Z/S	2/1 twill	12/7	brown	-	fulled	-	top edge turned over
TA/173	3517/134	4.0 X 6.5	W	Z/S	2/1 twill	13/10-11	rich brown	-	-	-	ragged
TA/174	3517/135	2.0 X 5.0, 1.5 X 8.0	W	Z/S	2/1 twill	12-13/10 14/10-11	brown	-	fulled	-	folded down middle folded centre and under at end
TA/175	3517/137	4.0 X 2.0	W	Z/S	2/1 twill	12/11	rich brown	-	-	-	
TA/176	3517/138	1 X 6, 1 X 8.5	W	Z/S	2/1 twill	11/9	brown	-	fulled	-	cut strips
TA/177	3517/139	6.0 X 1.2	W	Z/S	2/1 twill	11-12/8	dark brown	-	fulled	-	cut edges
TA/178	3517/140	3.5 X 2.5	W	Z/Z	2/1 twill	14/12	red-brown ?red	-	?fulled	-	warp & weft regular, very soft
TA/179	3517/142	c.11.0 X 3.0	?	Z/S	2/1 twill	9-10/10	dark rich brown	-	?fulled	-	warp fine, weave open, cut, fold parallel to one end
TA/180	3517/143	3.2 X 13.5	W	Z/S	2/1 twill	14/12-13	dark brown	-	fulled	-	slightly worn
TA/181	3517/147	4.0 X 6.5	W	Z/S	2/1 twill	12-13/10-11	dark brown	-	fulled	-	cut, with strip from one edge ?tailor's waste
TA/182	3517/148	c.4.0 X 6.5	W	Z/S	2/1 twill	13/9	mid brown	-	fulled	-	
TA/183	{ 3517/149 3656/47 4085/2	10 X 2, 4.5 X 1 6.0 X 0.8 19.0 X 0.8	W	Z/S	2/1 twill	12/9	very dark brown	-	fulled	-	warp well spun, regular weave bias-cut strip strip
TA/184	3517/151	c.12.0 X 1.5	W	Z/S	2/1 twill	16-18/13	dark grey brown	-	-	-	both yarns well spun
TA/185	3517/153	6.5 X 2.5	W	Z/S	2/1 twill	14-15/11-12	rich brown	-	-	-	warp very fine, weave loose
TA/186	3517/155	4 X 2.5, 7.0 X 1.5, c.1.5 X 6.0, 3.5 X 1.5	W	Z/S	2/1 twill	9-12/8	grey brown	-	fulled	-	
TA/187	3517/156	6.0 X 1.0	W	Z/S	2/1 twill	?/7-8	light grey brown	C.(fig.1.b), -	-	(x)	traces of stitches selvedge, damaged, 4 cords 3 warps each, 2 pairs; warp over- spun; no main weave
TA/188	3517/160	5 X 8, 6.5 X 3.5	W	Z/S	2/1 twill	12/10	dark brown	-	fulled	-	cut triangle, and rag
TA/189	3517/162	15.5 X 3.0	W	Z/S	2/1 twill	18-20/10	grey brown	-	fulled	-	warp very fine and close
TA/190	3517/165	10.0 X 2.0	W	Z/S	2/1 twill	12-14/10	dark brown	-	fulled	-	cut strip
TA/191	3517/166	3.5 X 2.7	W	Z/S	2/1 twill	14/12	crimson	-	fulled	(x)	has been turned and stitched one edge; both yarns fine, even
TA/192	3517/168	4.0 X 10.0	W	Z/S	2/1 twill	12-13/12	brown	-	fulled	-	triangular
TA/193	3656/18	13.0 X 2.0	W	Z/S	2/1 twill	16-17/12-13	pink-brown	-	fulled	-	cut strip, fine warp, solid weave

Cat.no.	Excavat.no.	Measurement	Fibre	Spin	Weave	Count	Colour	Borders	Finishing	Sewing	Remarks
TA/194	3656/19	9.5 X 4.5, 8 X 9, 14 X 6	W+	Z/S	2/1 twill	16/10-12	rich brown	-	?fulled	-	remains of shaping, edges turned under; wool fine and soft
	3656/58	3.5 X 11.0				16/14					
	3656/74	c.24.0 X 10.5				14-15/10					
TA/195	3656/35	1.1 X 17.0	W	Z/S	2/1 twill	16/11	brown	-	fulled	-	cut strip, folded lengthwise
TA/196	3656/37	4.0 X 2.5	W	Z/S	2/1 twill	11-12/7-8	light brown	-	-	-	weft coarse, variable; yarns unevenly pigmented or stained
	3656/51	6.5 X 8.0									colour patchy, ?dye deteriorated
TA/197	3656/39	9.5 X 3.5, 10.5 X 5, 6.5 X 3.5, 6.5 X 2.5	W	Z/S	2/1 twill	10/8	red*	C.1(1pr)	-	-	weave loose, open; 3 scraps
TA/198	3656/40	13 X 0.6, 13 X 0.6	W	Z/S	2/1 twill	est. 12/9-10	dark brown	-	fulled	-	cut strips, rolled or folded
TA/199	3656/41	c.10.0 X 3.5	W	Z/S	2/1 twill	?-10/3-9	yellow-brown	-	fulled	-	rectangle cut on bias
TA/200	3656/42	5.0 X 8.5	W	Z/S	2/1 twill	10/8	rich red-brown	-	fulled	-	
TA/201	3656/44	10 X 5, 10 X 0.8	W	Z/S	2/1 twill	11/10	rich brown	-	fulled	-	curved piece, and bias-cut strip
TA/202	3656/45	3.5 X 2.3	W	Z/S	2/1 twill	15-16/10-11	mid brown	-	fulled	-	fine regular yarn
TA/203	3656/46	9.5 X 8.0	W	Z/S	2/1 twill	13-14/10	dark brown	-	fulled	-	oval fragment
TA/204	3656/48	4.5 X 3.5	W	Z/S	2/1 twill	15/13-14	red-brown	-	fulled	-	fine regular spin, weave, cut triangle
TA/205	3656/50	10 X 7, c.2 X 8	W	Z/S	2/1 twill	12/10-11	bright brown	-	-	-	even spin, weave, matted and small scrap
	3656/78	3.5 X 4.5									good quality shiny wool
TA/206	3656/54	c.3.5 X 3.5	W	Z/S	2/1 twill	12/9-10	mid brown	-	-	-	
	3656/55	c.3.5 X 2.5				11/3-9					
TA/207	3656/57	3.5 X 11.0	W	Z/S	2/1 twill	16/14	brown	-	fulled	-	yarns fine, weave even, triangle
TA/208	3656/59	11.0 X 1.2, 3 X 4.5, 4 X 8 X 1, 2.5 X 7, 14 X 1	W	Z/S	2/1 twill	12-13/9-10	brown	C.1(i(4))	-	-	selvedge cord heavy, weft loops damaged; ragged matted scraps
TA/209	3656/60	6.5 X 3.3	W+	Z/S	2/1 twill	12-13/8	red-purple*	C.1(fig.1.e)	fulled	-	selvedge wefts drawing edge cords into hem; triangle
TA/210	3656/83	6.0 X 6.5, 4.0 X 3.0	W	Z/S	2/1 twill	12/6	dark brown	-	?fulled	-	strip ?darker than weft, fine, hard; weft soft; piece folded
TA/211	4085/3	c.2.8 X 3.0	W+	Z/S	2/1 twill	14/9	red*	-	-	-	?pre: Spanish merino
TA/212	4085/4	6.0 X 0.6	W	Z/S	2/1 twill	c.18/14 (8/7 on 5pr)	mid brown	-	fulled	-	
TA/213	3423/12	12.5 X 1.1, 6.0 X 1.0	W	Z/Z	2/1 twill	14-16/12	brown	C.1(fig.1.i)	-	x	selvedge 3 wefts; possible remains sewing thread
TA/214	3423/33	1.5 X 3.5, 4 X 2, 1.7 X 4.8	W+	Z/Z	2/1 twill	17/14	pale brown	C.1(fig.1.g)	-	-	very fine even yarn, soft, all selvedge with 2 wefts; small piece edge turned under
TA/215	3423/45	4.0 X 4.5	W	Z/Z	2/1 twill	6-8/6-8	grey brown	-	-	-	rather loose weave
TA/216	3423/50	3 X 12, 8 X 4	W	Z/Z	2/1 twill	20-22/10-22	brown	-	-	-	fine regular spin both yarns
TA/217	3423/57	2.5 X 9.0,	W	Z/Z	2/1 twill	15/12	pink-brown	-	-	-	fine soft wool, weft sometimes cross-hatched
TA/218	3423/61	5.5 X 3.4 X 4 14.0 X 0.6	W	Z/Z	2/1 twill	16/11	pale brown	C.1(fig.1.f)	-	-	the 2 fragments of the same material; extra threads and scraps

<u>cat.no.</u>	<u>excavation</u>	<u>measurement</u>	<u>Fibre</u>	<u>Spin</u>	<u>weave</u>	<u>Count</u>	<u>Colour</u>	<u>Borders</u>	<u>Finishing</u>	<u>Sewing</u>	<u>Remarks</u>
TA/219	3423/99	c.5.0 X 4.0	W	Z/Z	2/1 twill	15/10-11	red-purple*	-	-	-	yarns hard, weft overspun, some matting
TA/220	{ 4710/3 3424/14(a) 3424/48(a)	c.5 X 10, 6 X 4, 4.0 X 7.5 5.0 X 1.5 3.0 X 1.8	W+	Z/Z	2/1 twill	19/21 17/14 18/17	dark grey-brown	-	-	-	hard wool, fine regular spin, weaves, counts variable
TA/221	3424/25	c.8.0 X 5.0	W	Z/Z	2/1 twill	11/8	dark brown	-	-	-	matted; another fragment
TA/222	3424/42(a)	c.10.0 X 9.0	W+	Z/Z	2/1 twill	17/12	black*	-	-	-	wool hard, very regular spin weft overspun
TA/223	3517/141	6.5 X 3.0	W	Z/Z	2/1 twill	15/11	black(?blue)*	-	-	-	wool hard, overspun, even yarns, weave
TA/224	3517/146	21.5 X 2, 27 X 2.5	W	Z/Z	2/1 twill	15-16/12	rich brown	-	?fulled	-	even spin, weave, worn
TA/225	3573/2	19.0 X 21.0	W+	Z/Z	2/1 twill	19/15	brown	0.1(2)	-	-	selvedge 2 prs, (fig.1.a) but not coloured, yarns hard, shiny, weft slightly uneven
TA/226	3656/34	11 X 2.5, 6.5 X 1.5	W	Z/Z	2/1 twill	13/11	dark brown	-	fulled	-	regular spin, weave
TA/227	3656/86	5.5 X 3.0	W	Z/Z	2/1 twill	10-11/8	dark brown	-	fulled	-	cut edges, unworn, tailor's waste
TA/228	4085/1(b,c)	2.5 X 1.5	W	Z/Z	2/1 twill	13/16-17	bright brown	-	-	-	close even spin, weave; another scrap
TA/229	4089	3.0 X 4.5	W+	Z/Z	2/1 twill	19-20/13	brown	-	-	-	very hard shiny wool
TA/230	4909/2	5.2 X 5.2, 2.5 X 4.5	W+	Z/Z	2/1 twill	18-19/15	brown*	-	-	-	hard spun yarns, shiny
TA/231	3517/36	4.5 X 3.5	W+	S/S	2/1 twill	7-8/7-8	grey brown	-	fulled	-	cut edges
TA/232	3517/106	c.7.0 X 3.0	W	S/S	2/1 twill	10-11/9	bright brown	-	-	-	weave rather open, uneven, matted
TA/233	3517/161	6.5 X 3.5	W	S/S	2/1 twill	12-13/9	grey brown	-	fulled	-	triangle
TA/234	{ 3423/3 3517/112	3.5 X 3.0 9.0 X 7.5	W	Z/S, S	tabby extended tabby	8-10/4-5	pale brown/blue-black, (white) brown /yellow	- 0.1(2)	-	-	uneven; stripe 5 mm wide, 6 mm fine brown, over 2 warps
TA/235	3423/28	5.0 X 1.6	W	Z/S, S	tabby extended tabby	10/6-7	red-purple/dark brown, light grey brown	-	-	-	warp fine, weft coarse; one stripe 6 mm wide, 14 throws, light grey over 2 warps
TA/236	3423/68	c.5.5 X 5.5	W	Z/S	tabby	10-12/10	light tab/pink	-	-	-	matted
TA/237	{ 3656/30 3423/72 3656/67	c.12.0 X 5.5 c.5.5 X 3.5 12.0 X 6.0	W	Z/S	tabby	11/12-13	pale brown/pink-red gold-tab/	- 0.1(1)	?napped	-	weft alternate throws pale brown, pinky-red, raised nap pinkish; selvedge with one cord, 3 gold-tab warps, 4 pale brown as in warp

Cat.no.	Excavat.no.	Measurement	Fibre	Spin	Weave	Count	Colour	Borders	Finishing	Sewing	Remarks
TA/238	3423/77	5.5 X 2.5, 3.0 X 1.5	W	Z/S,	tabby	11-12/5	pale grey/dark brown, brown ?yellow	-	-	-	weft coarse (black fibres), stripe 4 mm, 3 ?yellow picks
TA/239	3424/51	1.5 X 12.5, 1.5 X 13.5	W	Z/S	tabby	9/6	pale brown/dark brown	-	?fulled	-	more matted; weft coarse, uneven
TA/240	3656/69	9.5 X 9.5, 5.0 X 4.0	W	Z/S, S	tabby extended tabby	9/10 24-26	pale brown/pale brown, dark pink-brown, ?dark yellow	-	?napped	-	weft alternate light and dark pink-brown; part of stripe, 1.1 deep, ?yellow over 2 warps
TA/241	3423/27	8.5 X 6.0	W/W, S	Z/S, Z Z, Sply extended t.	tabby	9-10/9	dark brown/dark brown, red-purple, ?yellow (W) ?yellow (S)	-	fulled	-	triangular; stripe 2.0 wide, 2 throws deteriorated silk, wool red-purple (Z), ?yellow 1.3, red-purple, 2 throws silk, over 2 warps
TA/242	3517/32	23.0 X 1.0 11.0 X 1.5	W/W, S	Z/S Z extended tabby	tabby	10-11/10	dark brown/dark brown ?yellow (S)	-	fulled	-	bias-cut strip, stripe 1.4 4 throws silk, 0.55 dark brown wool, 4 silk, 0.55 wool, 4 silk, all over 2 warps same fabric, no stripe
TA/243	3517/118	3.0 X 3.0 3.0 X 3.5	W/W, S	Z/S Z, Sply extended t.	tabby	8/11	pale brown/pale brown, brown (Z) ?yellow (S)	-	fulled	-	soft, variable weave; stripe both pieces, 3 mm wide, 6 rows silk, ?L brown wool, 6 silk; 2 small scraps
TA/244	3517/122	12.0 X 1.1	W/W, S	Z/S Z, Sply extended	tabby	?/8	rich brown/rich brown, dark brown ?yellow (S) (selvage)	1.1 (W) ?fulled	-	-	selvage strip, cords 2, Sply dark brown, then 2 pairs; only 2 main warps preserved stripe 5 mm, 4 throws silk, 4 wool, 4 silk, 4 wool, 4 silk 4 wool, 4 silk
TA/245	3656/11	9.0 X 7.0	W/W, S	Z/S Sply extended	tabby	9-10/10-11	pink-brown/pink brown* brown (Z) ?yellow (S)	-	-	-	rather open weave; narrow stripe 2 mm, 3 throw silk, 2 brown wool, 3 silk
TA/246	3656/97	4.5 X 1.2	W/W, S S	Z/S Sply	tabby	10/11	dark brown/dark brown ?yellow	-	fulled	-	stripe over single threads, 12 wide, ?warp direction, ?run in by needle, 2.5 mm.
TA/247	3656/98	15.0 X 2.7	W/W+ S	Z/S Sply extended	tabby	10-11/12-14	dark brown/dark brown pale brown ?yellow (S)	0.1 (S)	fulled	-	triangular, very similar to TA/246; 3 narrow silk stripe (7 throws each), 4.8 tabby main weave between; selvage 3 pale brown, Sply cords, 2 pairs. (see p.)
TA/248	3423/15	9.5 X 2.0	W	Z/S S extended	tabby	10/11	pale brown/pale brown, red ?purple	-	-	-	stripe 13 throws, 3.5 mm wide over 2 warps
TA/249	3423/16	12.0 X 6.0	W	Z/S	tabby	8/10	taupe-brown/taupe-brown,	-	?napped	-	stripe 2.2 wide, 1.1 deep

Cat.no.	Excavat.no.	Measurement	Fibre	Spin	Weave	Count	Colour	Borders	Finishing	Sewing	Remarks
TA/250	3423/17	11.0 X 2.5	W	Z/S	tabby	9-10/9	pink-mauve/pink-mauve	-	fulled	-	triangular; 2 light brown stripes, 6 throws each, 4-5mm
				S	extended tabby		light brown				
TA/251	3423/18	8.0 X 2.0	W	Z/S	tabby	10-11/10-11	brown/brown,	-	fulled	-	cut strip; stripe 4 throws
				S	extended tabby	26	?yellow, red				?yellow, 1.5 red, 4 throws yellow
TA/252	3423/20	4.5 X 3.0	W	Z/S	tabby	11/9	pale brown/pale brown	-	-	-	stripes one edge, 8 mm wide, 4 throws yellow, 2 red; 3
				S	extended tabby		yellow, red, ?mauve, brown				tabby; 2 throws ?mauve, 3 brown, 2 red, over 2 warps
TA/253	3423/22	c.8.0 X 3.0	W	Z/S	tabby	11/9	grey brown/grey brown	-	fulled	-	2.0 cm remaining stripe, purple; triangular
				S	extended tabby	20	purple				
TA/254	{ 3423/24	2.7 X 7.2	W	Z/S	tabby	10-11/9-11	dark brown/dark brown	-	fulled	-	stripe red-purple, 2.2 width preserved
	{ 3423/67	c.9.0 X 7.0		S	extended tabby	30	red purple				diamond-shape, turned under on 2 and possibly 3 sides, no stripe; ?gusset
TA/255	3423/25	3.5 X 4.3	W	Z/S	tabby	10/10	red-purple/red purple, C.1(2)	-	-	-	cut edges; 2 stripes (over pairs) red-purple 1.5, pale brown 1.4, 6 mm tabby between; selvedge cords first 4 warps, 2 red-purple, 2 brown, second ?3 brown
				S	extended tabby	24	brown pale brown				
TA/256	3423/26	11.0 X 2.2	W	Z/S	tabby	13/14-15	red or red-purple	-	fulled	-	very fine, weft overspun, self colour stripe 3 mm, 14 throws
				S	extended tabby						
TA/257	3423/29	3.0 X 1.0	W	Z/Z	extended tabby	6 prs/30-32	dark brown/dark brown, red-purple	-	fulled	-	from stripe, dark brown with 2 narrow red-purple
TA/258	3423/63	9.5 X 1.0	W	Z/S	tabby	10/10	grey brown/grey brown	-	?fulled	-	stripe 2.0 wide, darker fibre possibly only matted
				S	extended tabby	24	?darker brown				
TA/259	3424/2	4.5 X 9.0, 7 X 8.5, 5 X 2.3	W	Z/S	tabby	10-11/9-10	dark brown/dark brown,	-	-	-	on all bits, stripe 2.5 wide, 5 throws red, 5 buff, c.24 dark brown, 5 throws ?purple, 16 red, 5 throws buff, 5 red; purple (?black) decayed
				S	extended tabby	20-25	red, buff, ?purple black				
TA/260	{ 3424/3	2.5 X 9.0	W	Z/S	tabby	10-11/9-11	mid-brown/mid brown	-	?fulled	-	cut on curve, 4 mm tabby, stripe 4 mm brown, ?c.4 throws missing, 3 mm red, 4 mm brown with missing centre, 7 mm red, 2 brown. fragments also curved
	{ 3424/4	2.7 X 14.0 16.0 X 3.5		Z,S/S			black-brown	C.1(1)			one with selvedge, cord 4 coarse 3 darker warps, 1 pr. main warp; both with same stripe, one edge turned under

Cat.no.	Excavat.no.	Measurement	Fibre	Spin	Weave	Count	Colour	Porters	Finishing	Sewing	Remarks
TA/261	3474/5	10 X 17.5, 4.0 X 2.3	W	Z/S Z	tabby extended tabby	9/10-11 24	brown/brown, pink, brown	-	-	-	both pieces stripe 2.1 wide brown(S) 7 mm, pink(Z) 7 mm brown(S) 7 mm
	3656/6	6.0 X 33.5				12-13/10				(x)	piece turned over, stitch-marks, long side; no stripe
TA/262	3424/6	6.2 X 10.0	W	Z/S S	tabby extended tabby	9/11 18(5mm)	light brown	-	-	-	stripe 5 mm wide, fine light brown yarn
TA/263	3424/7	10.0 X 9.0	W	Z/S S, Z extended	tabby tabby	10-11/10-11	dark brown/dark brown, ?pink, mid-brown, light brown	-	-	-	stripe 2.3 wide, 4 throws lt. brown(S), 7 mm ?pink(Z), the stripes c.4 throws each, light brown, pink, mid-brown
TA/264	3424/8	3.0 X 4.0 3.5 X 10.0	W	Z/S	tabby	11/12-13	dark brown/dark brown, red or red-purple, ?orange	-	fulled	-	stripe 1.1 wide, ?orange between narrow red-purple bands; fine regular weaves; bias-cut strip, no stripe
TA/265	3424/11	1.8 X 23.0 10.0 X 0.8	W	Z, S/S S	tabby extended tabby	10-11/9-10 ? c.12	pale brown/brown, red	3.1(5)	fulled	-	fragment selvage, cords 15, 12 paired; brown main weave
TA/266	3424/12(a)	31.0 X 1.2 2.5 X 32.0, 2.0 X 3.5	W	Z/S S	tabby extended tabby	10/10-11	mid brown/mid brown, red	-	fulled	-	4.0, stripe red 4.6 over 2 warps, rest brown cut strips, remains stripe 3 mm wide, 4 mm brown, 4 red other small scraps
TA/267	3424/12(b)	1.1 X 14.0	W	Z/S S	tabby extended tabby	11/14	rich brown, rich brown, dark brown	-	?fulled	-	5 mm width of stripe preserved at one edge, 2 mm dark brown 2 mm same as main weave, over 2 warps
TA/268	3517/21 3517/22	17.0 X 1.5 17.0 X 1.7	W	Z/S S	tabby extended tabby	9-10/9-10 24	dark brown/dark brown, dark brown*	-	fulled	-	cut strip, 1.4 of stripe and strip folded down middle, 2 stripes 5.3 apart, one complete 3.0 wide; colour now near to main weave
TA/269	3517/24 3517/29	20.0 X 1.5 0.8 X 12.0 21 X 1.9, 12 X 1.5	W	Z/S	extended tabby	1-5prs/?	dark brown/brown, crimson*	-	fulled	-	strip folded middle, no stripe fragment stripe, brown 2mm, crimson 5 mm, brown
TA/270	3656/92(a)	12.0 X 2.0	W	Z/S S	tabby extended tabby	9-11/9-11	dark brown/dark brown*, dark brown*	-	fulled	-	2 strips, folded lengthwise near middle
TA/271	3517/34 3517/44 3517/110 3517/46	11.0 X 1.3 35.0 X 1.4 6.5 X 7.2 3.2 X 3.2.5 X 2.5	W	Z/S S	tabby extended tabby tabby	10/10 11-10/10	grey brown/grey brown, dark brown, beige	-	-	-	strip, stripe present 1.5. colour like main weave, but madder (p.); strip, end turned under; strip triangle; stripe 2.5 wide, 5 mm dark brown, 8 beige, 3 to

<u>Date.</u>	<u>Excavat.no.</u>	<u>Measurement</u>	<u>Fibre</u>	<u>Spin</u>	<u>Weave</u>	<u>Count</u>	<u>Colour</u>	<u>Borders</u>	<u>Finishing</u>	<u>Sewing</u>	<u>Remarks</u>
TA/272	3656/75	7.0 X 3.5	W	Z/S	tabby	10/10	mid brown/mid brown	-	fulled	-	ragged remains 1.0 red-purple stripe fragments, cut edges
	3517/48	14 X 2.5, 4.8 X 3, 1.8 X 2.5, 3 X 1.4		S	extended tabby	11-12/10-11	red-purple				
TA/273	3517/68	9.0 X 8.0	W	Z/S	tabby	11/10-11	rich brown/rich brown	40.1	-	-	very uneven weft; one torn end, 2.0 of stripe, self-colour over 2 warps; torn edge, 3 warp pairs ?from selvedge
				S	extended tabby	/20	?rich brown				
TA/274	3517/111	5.7 X 9.5	W	Z/S	tabby	10/8	crimson/crimson,	-	?fulled	-	across middle, stripe 8 mm green, ?11 throws
				S	extended tabby		green				
TA/275	3517/113	14.0 X 5.0	W	Z/S	tabby	10/10	brown/brown	-	?fulled	-	triangle, long edge turned under; near wider end, 2 stripes, each 1.0 wide, 8 mm tabby between, one crimson, one grey brown
				S	extended tabby	/26	crimson, light grey brown				
TA/276	3517/114	2.5 X 2.4	W	Z/S	tabby	11/7	crimson/crimson, brown,	-	-	-	1.7 tabby, brown weft ?stripe narrow brown edge over 2 warps; 6 mm crimson tabby
				S	extended tabby		brown				similar crimson tabby, stripe 6 brown wefts over 2, then brown tabby; selvedge cords each 43, red with pale brown and 2 3 pale brown
		7.4 X 1.7		Z, S/S			crimson, pale brown	2.1(1)			
TA/277	3517/115	4.5 X 7.5, 6.5 X 7.5	W	Z/S	tabby	10/11	brown/brown,	-	fulled	-	both bias-cut, with crimson stripe 2.0 wide
				S	extended tabby	/22	crimson				
TA/278	3517/116	3.5 X 3.5	W	Z/S	tabby	9/9	red-brown/red-brown, C.1(2)	-	-	-	cut curved; stripe 2.5, 5 crimson throws, centre pale brown, 5 crimson; scrap selvedge cords pale brown
				S	extended tabby	/22	pale brown, crimson, pale brown				
TA/279	3517/117	6.7.5 X 2.0	W	Z/S	tabby	10/8	dark brown/dark brown,	-	-	-	spin weave open, matted; stripe 2.5 wide, brown 3 mm, 3 picks black, 3 red, 10 brown, 3 red, 3 black, 8 mm brown
				S	extended tabby		brown, black, red				
TA/280	3517/119(b)	15.0 X 1.0	W	Z/S	tabby	9/10	dark brown/dark brown	-	fulled	-	strip, fragment stripe 11.3 wide, pale brown, crimson 2.5 mm only preserved
				S	extended tabby		crimson, pale brown				
TA/281	3656/00	5.0 X 5.0, 5.0 X 8.0	W	Z/S	tabby	8-9/9-10	rich brown/rich brown	-	-	-	2 fragments, stripe 7 mm wide brown with 4-6 pink picks in centre; (b) 1.2 width brown
	3656/32	5.0 X 1.5 (b)		S	extended tabby	/c.20	rich brown, pink-red				stripe. 3 deteriorate, scraps
	3656/28	4 X 1.5, 4 X 4, 4.0 X 3, 4 X 4, 2.5 X 1.3									edges turned under, slightly
											edges;

Cat.no.	Excavat.no.	Measurement	Fibre	Spin	Weave	Count	Colour	Borders	Finishing	Sewing	Remarks
TA/282	(3656/94 3656/27)	2.5 X 4.0 11.5 X 3.0, 10.0 X 1.5	W	Z/S Z/S	extended tabby tabby	4prs/24 10/11	warm brown/brown* warm brown	-	?fulled	-	part stripe, soft yarn cut edges, piece at right angles; other scraps
TA/283	3656/33	7.0 X 0.6	W	Z/S	extended tabby tabby	5-6prs/ 11/	brown/brown, red	-	fulled	-	scrap cut from stripe, tabby 3 mm, red stripe 3 mm
TA/284	3656/92(b)	4.3 X 9.0	W	Z/S S	tabby extended tabby	9/8 /20	rich brown/rich brown rich brown	-	fulled	-	triangle cut, stripe, same brown, depth 2.0 preserved
TA/285	3656/95	10.9 X 24.0 5.0 X 2.5	W+	Z/S S	tabby extended tabby	8-9/7-8	pale brown/pale brown brown, red	-	?napped	-	rather open weave; 3.0 tabby stripe 4 throws brown, 4 red; 3.7 tabby; stripe 3 throws brown, 4 red; 3.0 tabby piece with 4 throws brown, 4 red. ?"raie"(p.
TA/286	3656/96	1.0 X 4.0	W	Z/S S	tabby est.10/8 extended tabby	12(5mm)	dark brown/dark brown,* light brown	-	-	-	4 mm only main weave, stripe lighter
TA/287	3656/101	7.5 X 3.5	W	Z/S S	tabby extended tabby	11/6-7 /22	pale brown/pale brown dark brown, ?natural, purple	-	-	-	warp finer than weft; stripe 2.2 wide, 4 throws dark brown 4 natural, 4 dark, 1.5 cm ?purple, dark brown, natural, dark brown as above
TA/288	3656/102	2.8 X 2.5	W	Z/S Z, Sply S	tabby extended tabby	12/10 /16	pale brown/pale brown red sel, bright br. C.1(3)	-	-	-	stripe 1.0, 5 throws bright brown neither side red centre selvedge 3 red plyed cords on both, parts stripe, 2.3 wide
TA/289	3656/103	2.0 X 10.5, 6.0 X 4.5	W	Z/S S	tabby extended tabby	3/12 /26	warm brown/warm brown ?yellow	-	-	-	wide
TA/290	3423/31	20.0 X 5.5	W	Z/S Z, Sply	tabby	11/11-13	mixed brown, black ?yellow	C.1(3)	-	-	mixed fibres; selvedge 3 ?yellow cords, 2 main pairs
TA/291	3423/75	3.5 X 5.8, 8.5 X 2.5	W	Z/S Z, Sply	tabby	12/9-11	pinkish-red grey-brown/	C.1(5)	-	-	selvedge one piece, grey plyed cords, 5
TA/292	3423/81	6.5 X 1.2, 4.5 X 1.2	W	Z/S	tabby	12/11	pinkish-red brownish/	C.1(2)	-	-	2 scraps selvedge, 2 coarse edge threads browner; ? opposite selvedge TA/291
TA/293	3423/100	3.0 X 2.5, 3.8 X 1.5	W	Z/S Z, Sply	tabby	10/11	red-brown ?red yellow brown/	C.1(5)	?fulled	-	selvedge both pieces 6.5 mm wide, 5 ?yellow threads
TA/294	3517/22	17.0 X 0.8, 13.5 X 0.8	W	Z/S Z, Sply	tabby	? /8	pinkish-purple* black-purple/*	C.1(6)	-	-	selvedge strips, 6 black-purple one pr main pink-purple
TA/295	3656/5	10 X 1.2, 19 X 1, 5.5 X 1.5, 30.0 X 1.0	W	Z/S Z, Sply	tabby est.10/10		dark red brown/	C.1(6)	-	-	warp and one single 4 selvedge strips, 6 brown threads followed by 2 red pairs
TA/296	3423/13	26.0 X 1.4	W+	Z/S	tabby	?/8	mid-brown/brown?	C.1(M.1.3)	fulled	-	horn strip, very coarse weft, slightly darker, 1.5 cm wide selvedge

<u>Cat.no.</u>	<u>Excavat.no.</u>	<u>Measurement</u>	<u>Fibre</u>	<u>Spin</u>	<u>Weave</u>	<u>Count</u>	<u>Colour</u>	<u>Borders</u>	<u>Finishing</u>	<u>Sewing</u>	<u>Remarks</u>
TA/297	3423/23	11.0 X 2.0	W	Z/S	tabby	10/8	brown	-	fulled	-	?facing, bias-cut strip, turned under at sides
TA/298	3423/54	5.0 X 1.3	W	Z/S	tabby	13-14/11	red-purple	-	?fulled	-	
TA/299	{3423/58 3423/55 3517/24	4.0 X 2.0 13 X 1, 5.5 X 0.8 3.0 X 1.7	W	Z/S	tabby	10-11/10-11	dark rich brown	-	?fulled	-	cut strips, slightly curved worn; another scrap
TA/300	3423/59	10.0 X 2.0	W	Z/S	tabby	9-10/9	brown	-	fulled	-	spinning uneven
TA/301	3423/64	14.5 X 3.0	W	Z/S	tabby	12/12	red-purple	-	fulled	-	strip, ?facing, turned under end and one side; 6 small strips and scraps
TA/302	3423/65	6.0 X 2.4	W	Z/S	tabby	10/10	red-purple	-	fulled	-	similar, coarser, may be 301
TA/303	3423/66	6.5 X 2.5	W	Z/S	tabby	14/14	red-purple	-	fulled	-	bias cut, finer, as 301,302
TA/304	3423/69	10.0 X 2.0	W	Z/S	tabby	10-11/8-9	brown	-	fulled	-	strip, turned under long edges
TA/305	{3423/93 3423/73(a) 3423/74	2.5 X 2.5, 5 X 2, 2.0 X 3.0 4.5 X 5.5 11 X 3, 11 X 7	W+	Z/S	tabby	12-14/12-14	pale brown	-	fulled	-	fine even spin, weave; four fragments, one small and scrap
TA/306	{3423/74 3656/56	4.5 X 10, 13 X 5	W	Z/S	tabby	15/12, 15/9 14/10, 13/12	brown*	-	?fulled	-	yarn shiny where clear; scraps
TA/307	{3423/77(a) 3423/71(b) 3656/71	1.5 X 2.5 0.5 X 3.5 3 X 3, 7 X 1	W	Z/S	tabby	11-12/12 14/11 13/13, 13/11	yellow-brown	-	fulled	-	cut fragment, variable weave strips
TA/308	{3423/76 3424/57(b)	6.0 X 1.7 10.5 X 8.0	W	Z/S	tabby	11-12/10-11	rich brown	-	fulled	-	even spinning and weaving
TA/309	3423/78	2 X 5, 3 X 2.5	W	Z/S	tabby	14-15/11-13	red	-	fulled	-	fine uneven
TA/310	3423/79	2.0 X 3.5	W	Z/S	tabby	14/14	red	-	fulled	-	fine spin, weave
TA/311	3423/80	6.2 X 3.2	W	Z/S	tabby	12/9	red	-	fulled	-	scraps, best triangle, edge turned under
TA/312	{3423/34 3423/39 3423/91	3.5 X 2.4, 7 X 4 0.10.0 X 5.0 0.0 X 7.0	W	Z/S	tabby	10-12/11-12 12/10 13/12	brown	-	fulled	-	both yarns uneven; cut edge
TA/313	{3423/86 3423/85	0.17.0 X 1.5 3.0 X 2.0	W	Z/S	tabby	11-13/11-13 10/9	dark brown	-	fulled	-	bias cut one edge turned under
TA/314	{3423/91 3517/85	0.17.0 X 1.5 0.0 X 2.5	W	Z/S	tabby	12/12, 13/5 17/12	pale red-brown	-	?fulled	-	cut edges; fine thread
TA/315	3423/95	6.5 X 5.5	W+	Z/S	tabby	9/10	dark brown	-	-	-	soft wool, discoloured, weave open
TA/316	3423/96	6.0 X 3.0	W	Z/S	tabby	11-12/12-14	pink-red	-	?snapped	-	both yarns uneven
TA/317	3423/102	6 X 2, 7.5 X 2.2	W	Z/S	tabby	10/10	mid-brown	-	fulled	-	5 fragments, one edges folded, used as bias facing
TA/318	3423/104	5.0 X 1.2	W	Z/S	tabby	? /9-10	?red	0.1	-	-	served as strip, 2 coarse, 1 pr. 2 singles, 2 prs, only 4 main wps
TA/319	3424/17(c)	7.0 X 1.5	W	Z/S	tabby	9/9	brown	-	fulled	-	one edge turned under
TA/320	{3424/53(b) 3424/53(c)	5.0 X 3.0 15.0 X 6.0	W	Z/S	tabby	12/12-13	rich brown	-	?fulled	-	fairly even spin, weave

TA Catalogue.

Cat.no.	Excavat.no.	Measurement	Fibre	Spin	Weave	Count	Colour	Borders	Finishing	Sewing	Remarks
TA/321	3424/41(b)	7.5 X 2.5, 2.0 X 3.5	W	Z/S	tabby	11-12/10	red-brown	-	fulled	-	very fine wool; curved, turned under; a third scrap
TA/322	3424/41(d)	6.0 X 2.7	W	Z/S	tabby	11/9	brown	-	fulled	-	triangle, edge turned under; scrap
TA/323	3517/45	c.63.0 X 2.0	W	Z/S	tabby	11-12/9	grey-brown	-	fulled	?x	strip; long pale brown Sply silk thread tangled round it
	3424/43(a)	14.0 X 1.8				10/10					cut ppointed strip
TA/324	3424/43(b)	12.0 X 2.0	W	Z/S	tabby	13-14/11	mid-brown	-	fulled	-	long strip
TA/325	3424/43(d)	6.5 X 3.0	W	Z/S	tabby	10/11	red-brown	-	fulled	-	triangle
TA/326	3424/45	8.0 X 2.6	W	Z/S	tabby	12/13-14	pale mid-brown	-	fulled	-	rectangle, cut; yarns fine
TA/327	3424/47	4 X 18, 12 X 2	W+	Z/S	tabby	11-13/13, 11/9-10	mid-brown	-	-	-	matted
TA/328	3424/48(b)	6.0 X 3.0	W	Z/S	tabby	10-11/9	pale grey-brown	-	?fulled	-	some light fibres, ?white
TA/329	3424/49(a)	7.0 X 12.0	W	Z/S	tabby	12-13/13-14	purple-brown	-	fulled	-	good broadcloth; and tiny scrap
TA/330	3434/49(b)	9.0 X 8.5	W	Z/S	tabby	11/11	rich brown	-	fulled	-	pinked edge probably from seam, part turned under; another bit
TA/331	{3424/50(a)	14.0 X 4.0	W+	Z/S	tabby	11/11-12	pink-brown	-	fulled	-	cut edges; fibres unevenly
	{3424/53(d)	1.8 X 21.0				12-13/13					coloured; and scrap
TA/332	3424/50(c)	6.5 X 5.0	W	Z/S	tabby	10-11/12	mid-brown	-	fulled	-	
TA/333	3424/50(d)	3.0 X 3.5	W	Z/S	tabby	10/9	mid-brown	-	fulled	-	deteriorated
TA/334	{3424/50(e)	10.0 X 2.0	W	Z/S	tabby	12/11	mid-brown	-	fulled	-	good quality weave
	{3424/53(e)	6.0 X 1.8				13/9-10					
TA/335	3424/52	11.0 X 4.5	W	Z/S	tabby	12/11	brown	-	fulled	-	good broadcloth; curve turned under
TA/336	3424/53(f)	1.0 X 17.5	W	Z/S	tabby	10/10	brown	-	fulled	-	uneven spin, weave
TA/337	3424/55	2.0 X 4.0	W	Z/S	tabby	11/3	dark brown	-	fulled	-	or maybe
TA/338	3424/56(b)	16.0 X 2.0	W	Z/S	tabby	12/10-11	brown	-	fulled	-	bias-cut strip
TA/339	3424/57(c)	c.14.0 X 10.0	W	Z/S	tabby	12/10-11	gray-brown	-	fulled	-	
TA/340	3424/59(b)	c.21.0 X 11.0	W	Z/S	tabby	12/10	brown	-	-	-	uneven spin, weave; matted; fold-marks
TA/341	{3517/14(a,c)	11 X 0.7, 2 X 0.7	W	Z/S	tabby	11-12/10	dark brown*	-	fulled	-	cut strips, ?tailor's waste
	{3517/26	16.0 X 1.3				9/10					tapering strip
	{3517/119(a)	46 X 1.5, 13 X 2				9-10/11					
TA/342	{3517/14(b)	14.0 X 1.5	W	Z/S	tabby	9-12/10	dark brown*	-	fulled	-	strip, folded for use as bias
	{3556/91	1.5 X 13.0									binding? and cut strip
TA/343	3517/18	3.0 X 3.1	W	Z/S	tabby	10/11	mid-brown	-	fulled	-	cut rectangle
TA/344	3517/19	3.0 X 1.2	W	Z/S	tabby	10-11/10	rich brown	-	fulled	x	cut strip, marks stitches one edge, fragment 1, Sply silk thread other
TA/345	3517/20	6.0 X 2.8	W	Z/S	tabby	10/11-12	red-brown	-	fulled	-	triangle, cut edges
TA/346	{3517/23	c.17.0 X 8.5	W	Z/S	tabby	14/14	gray-brown	-	fulled	-	regular weaving; cut edges
	{3517/27	c.9.0 X 7.5				13/12					cut triangle
TA/347	3517/25	2.6 X 2.4	W	Z/S	tabby	14/9	dark brown	3.1(2)	fulled	-	strip cut, selvedge 2 yds long
TA/348	3517/27	9.5 X 3.7	W	Z/S	tabby	14/14-15	very dark brown	-	fulled	-	fine, very regular, cut along

Cat.no.	Excavat.no.	Measurement	Fibre	Spin	Weave	Count	Colour	Borders	Finishing	Sewing	Remarks
TA/349	3517/30	11.0 X 3.0	W	Z/S	tabby	10/11	dark brown	-	?fulled	-	triangular cut strip, worn thin
TA/350	3517/31	11.0 X 3.2	W	Z/S	tabby	13/11	yellow-brown	-	-	-	cut, shape suggests neckband
TA/351	3517/32	30.0 X 1.0	W	Sply, Z/S	tabby	? 5/9-10	dark brown	1.1(8)	fulled	-	strip selvedge, 3 plyed warps, torn
TA/352	3517/33	6.5.0 X 2.0	W	Z/S	tabby	11/11	rich brown	-	?matted	-	cut edges
TA/353	3517/34	7.0 X 1.8	W	Z/S	tabby	11/10	rich brown	-	-	-	-
TA/354	3517/41	4.5 X 5.0	W	Z/S	tabby	10/9	brown	-	matted or fulled	-	worn
TA/355	3517/42	0.9 X 11.0	W	Z/S	tabby	12/7	brown	-	matted or fulled	-	uneven, 2 yarn regular, S coarse as in 2/1 twills
TA/356	3517/43	5.0 X 4.4	W	Z/S	tabby	10/11	pink-brown?red	-	-	-	matted, fine yarns, regular weave
TA/357	3517/47	4.4 X 4, 8 X 1.8	W	Z/S	tabby	11-13/12-13	red-brown?red	-	?matted	-	cut fragments, matted
TA/358	3517/50	10.0 X 1.5	W	Z/S	tabby	12/10-11	rich brown	-	fulled	-	pointed fragment
TA/359	3517/51	12.5 X 1.0	W	Z/S	tabby	11/11	red-brown,?red	-	fulled	-	new tailor's waste, cut on curve
TA/360	3517/52	10.5 X 1.5	W	Z/S	tabby	12/10	rich brown?red	-	fulled	-	cut strip, worn
TA/361	3517/54	4.0 X 2.7	W	Z/S	tabby	11/12	dark red	-	matted or fulled	-	regular weaving
TA/362	3517/55	11 X 0.9, 7.5 X 0.7	W	Z/S	tabby	est. 12/12-13	dark brown	-	fulled	-	bias-cut strips
TA/363	3517/57	X	W	Z/S	tabby	12/12	red-brown	-	fulled	-	strip cut on curve
TA/364	3517/58	12.0 X 0.3	W	Z/S	tabby	10-11/3-9	rich brown	-	fulled	-	2 fragments together wedge-shaped
TA/365	3517/61	6.5.0 X 13.0	W	Z/S	tabby	9/11	dark brown	-	-	-	2 yarn more pigmented or patchily dyed
TA/366	3517/63	1.0 X 11.0	W	Z/S	tabby	10-11/11	dark brown	-	fulled	-	cut edge
TA/367	3517/68	12.5 X 1.5	W	Z/S	tabby	12/10	light brown	0.1(1)	-	-	fragment selvedge, 2 Z pairs, 1 Sply threads
TA/368	3517/69	7.7, 11.0, X 3.6	W	Z/S	tabby	13/11	rich brown	0.1(1)	fulled	-	selvedge 3 paired warps
TA/369	3517/70	6.6 X 3, 6.6 X 3	W	Z/S	tabby	12/10	dark brown	-	fulled	-	1, triangular
TA/370	3517/71	5.0 X 1.7	W	Z/S	tabby	12/11	red-purple	-	?fulled	-	very even spin, weave; matted
TA/371	3517/72	6.4.0 X 5.0	W	Z/S	tabby	14-15/11-13	dark crimson	-	fulled	-	cut oval, very even spin, weave
TA/372	3517/91	5.5 X 3.2	W	Z/S	tabby	12-13/9	pink-brown	-	-	(#)	weave regular; top edge turned over
	3517/78	6.0 X 11.5	W								stitch-marks; outer ragged bit
TA/373	3517/79	7.0 X 7.0, 2.5 X 4.0	W	Z/S	tabby	10-11/9-11	red n, mixed	-	-	(#)	one edge possibly sewn? weave loose, varying pigmentation?
TA/374	3517/80	8.5 X 5.0	W	Z/S	tabby	10-11/10-11	red-brown	-	-	-	very uneven weft
TA/375	3517/83	7 X 3.5, 6 X 3.5	W	Z/S	tabby	9-10/3-6	red	-	fulled	-	cut edges; warp fine, weft coarse
	3517/7	11 X 2.5, 5.5 X 2.5	W			9-10/7-8					irregular as in 2/1 twills; weft threads double in 3 places, ?correcting weaves ("red, as")
TA/376	3517/84	2 X 2, 1.5 X 1.2	W	Z/S	tabby	10/6-9	dark brown	-	?fulled	-	very matted; and small scrap
TA/377	3517/86	7.5 X 3.0	W	Z/S	tabby	12/12	black-purple	-	-	-	slight marring
TA/378	3517/89	1s. 7.5, 9.5, 5.0 width 1.2-0.9	W	Z/S	tabby	12/12	black-tan	-	?fulled	-	three strips, varying width, even spin, weave
TA/379	3517/90	8.0 X 2.0	W	Z/S	tabby	14/11	brown	-	fulled	-	-
TA/380	3517/93	8.5 X 1.5	W	Z/S	tabby	10/10	black, ?purple	-	fulled	-	regular rather open weave, one edge turned under

Cat.no.	Excavat.no.	Measurement	Fibre	Spin	Weave	Count	Colour	Borders	Finishing	Sewing	Remarks
TA/381	3656/3	9 X 9, 12 X 4, 4.0 X 2.0	W	Z/S	tabby	12/12	red-brown?red	-	fulled	-	
TA/382	3656/4	40 X 2, 29 X 1.5 25.0 X 1.8 15.0 X 2.0	W	Z/S	tabby	10-12/10-12	rich brown	-	fulled	-	?new tailor's waste, 2 bias-cut, cut in semicircular strip, and 8 smaller cut strips
TA/383	3656/12	11.0 X 5.0	W	Z/S	tabby	10/7	mid-brown	-	fulled	-	triangle, cut edges
TA/384	3656/13	16 X 1.8, 12 X 1.2	W	Z/S	tabby	10-11/10	red-brown*	-	fulled	-	and small scrap, all cut edges
TA/385	3656/22	3.3 X 14.0	W	Z/S	tabby	10-11/10-11	red-brown	-	fulled	-	cut triangle
TA/386	{ 3656/24 3656/34	4 X 2, 7.5 X 1.3 3.0 X 3.5	W	Z/S	tabby	11-12/12 10-11/10	rich brown	-	napped or fulled?	-	and another scrap
TA/387	{ 3656/25 3656/38 3656/73	2.3 X 1.8, 5 X 1, 4.5 X 5.5, 4 X 3, 1.5 X 3 9.0 X 2.5 11.5 X 8.0	W	Z/S	tabby	11-13/10-12 11/9	mid pale brown*	?napped	-	(x)	scraps, even spin, weave, one side clear; one with traces stitches and fold; and very long narrow strip long triangle, cut edges
TA/388	3656/29	11 X 24, 2.5 X 3.5 1.0 X 12.0	W	Z/S	tabby	13-14/12-13	pale pink-brown	-	fulled	(x)	triangle, turnover / traces stitches long side; fine spin, weave
TA/389	3656/31	15.0 X 2.0	W	Z/S	tabby	12/12	red-brown?red	-	fulled	-	bias-cut
TA/390	3656/35	11.0 X 5.0	W	Z/S	tabby	13/12-13	rich brown	-	fulled	(x)	cut curve, stitch-marks at edge
TA/391	3656/66	2.5 X 4.0	W	Z/S	tabby	9/10	rich brown	-	-	-	open weave; and narrow strip
TA/392	3656/77	5.5 X 7, 2 X 2.5, W 30.0 X 19.0	W	Z/S	tabby	9-10/9-10	black-brown	-	?napped	-	
TA/393	3656/87	20.0 X 0.7	W	Z;Z, Sply/3	tabby	? / c.10	pale brown	2.1(4)	fulled	-	selvage strip, 2 cords plyed strips
TA/394	3656/1	1.3 X 9.5	W	Z/S	tabby	12/11	dark brown	-	fulled	-	cut strip
TA/395	3623/92	c.4.0 X 25.0	W	Z/Z	tabby	13/11	pale brown	-	-	-	long ragged triangle, rather loose uneven weave
TA/396	3624/37(1)	6.5 X 2.5	W	Z/Z	tabby	10/10	pale brown	-	fulled	-	
TA/397	3517/60	c.11.0 X 2.5	W	Z/Z	tabby	11/9	dark brown	-	-	-	slightly matted
TA/398	3517/77	c.18.0 X 3.5	W	S/S	tabby	11/11	black*	-	-	-	long tapering triangle
TA/399	{ 3517/92 3517/62	11.5 X 4.5, 6.5 X 2.5 4 X 3, 4.5 X 3.5	W+	S/S	tabby	13/10	black-brown*	-	-	-	ragged

Cat.no.	Excavat.no.	Measurements	Fibre	Spin	Technique	Trade or count	Colour	Sewing	Remarks
TA/400	3665.2740	Length 11.0, circum.c.90.0	S	Z,Sply	netting, knotted	mesh 5 mm	dark brown		hair net, very fine silk, tubular; loops round edge, 1.3 cm long, threaded on strand of 4 coarse Sply silk threads, loops taken alternate from the 2 sides when the net is folded flat, thread knotted in circle; other end of net, silk braid, torn in middle, sewn Sply brown silk, each stitch picking up 1 loop from net; finger loops still at end of braid. (Pl. , p. ? <i>handing arm ends.</i>)
		Length 29.0, width 2 mm	S	Z,Sply	finger-loop braid	5 loops	dark brown	x	
			S	Sply	-	-	pale brown	x	
TA/401	3665.2700	L.c.12.0	S	Z,Sply	netting, knotted	mesh 1.0	light brown	-	hair net, fragment; loops strung on coarse thread mixed light and dark fibres
TA/402	3517/1	L.6.5, circ.1.1	S	Z,3ply	square cord	10 threads	light brown	-	made on tablets or bobbins (p.
TA/403	3516/3172	L.18.0, wid.5.5mm	S	Z,Sply	finger-loop braid	6 loops	light brown	-	
TA/404	4091/1	L.32.0, width 2 mm	S	Sply	finger-loop braid	5 loops	?natural	-	loops double Sply threads, well preserved; braid knotted one end
TA/405	4091/2	L.25.0, width 3mm	S	Sply	finger-loop braid	5 loops	dark brown, light brown	-	5 loops dark, 2 light brown
TA/406	4091/4	L.12.0 circ. 8 mm	S	S	square plait	712 threads	dark brown*	-	threads worked in 3s, deteriorated (see TA/407)
TA/407	4093/1	L.6.5, circ.5 mm	S+	Z	square plait	12 threads	?natural	-	12-thread braid, worked in 3s (fig. one end knotted
TA/408	4005/2(a)	L.17.0, circ.3 mm	S	Z,Sply	finger-loop	5 loops	dark brown	-	
	(b)	L.17.5, circ.3 mm	S	Z,Sply	braid	5 loops	dark brown	-	fragment similar braid, tied to small piece (c)
	(c)	L.c.7.0, width	S	Z,Sply	flat braid	9 threads	red-brown	-	more deteriorated, (fig.) tied to 13.0 long piece (a)
TA/409	3696.6702	L.13.0, circ.2.8-3	?G+	S,Zply	threads	-	black	-	coarse black thread or string
TA/410	3423/1	L.70.0, 33.0, 20, 13 circ.1.0-1.1	W or G+	S,3ply	string	-	red brown	-	lengths string, S spin slight
TA/411	3697.2787		S+	Z,Sply	threads ?fringe	-	brown	-	lass threads, in four places tied in bunches of 12, ?rug fringe
TA/412	3668.2789	L.12.0	W	Z,Sply	threads, ?fringe	6-8 loops	dark brown	-	mass threads, divided into 2 bunches knifing in loops, Splied, and ends shorter, twisted together 2

<u>Cat.no.</u>	<u>Excavat.no.</u>	<u>Measurements</u>	<u>Fibre</u>	<u>Spin</u>	<u>Technique</u>	<u>Grade or count</u>	<u>Colour</u>	<u>Sewing</u>	<u>Remarks</u>
TA/413	3009.277.	L.40.0, circ. 0.7-1.0	W	S, Zply	threads	-	dark brown, mid brown	-	2 tied loosely in a loop with a finger knot
TA/414	4066	L.c.14.0	W	S	threads	-	dark brown	-	mass thread ends, some overspun, ?warp ends
TA/415	4067/1	L. 9.0	W	Z	threads?fringe	-	brown	-	coarse, pairs twisted together with ?unspun wool
TA/416	4067/2	L.13.0	W	Z, Sply	threads	-	brown	-	in bunch; ?warp ends
TA/417	4067/3	L.c.8.0	W	S	threads	-	mixed browns	-	tangle mixed threads, some fine
TA/418	4067/4	L.9.0	W	S & Sply	threads	-	dark brown	-	2 coarse threads, ?blanket quality
TA/419	4067/5	-	W	S & Sply	threads	-	brown	-	mass similar thread ends
TA/420	4067/6	L.20.0, 20.0	W+	S, Zply	threads	-	dark brown	-	three, coarse
TA/421	4067/7	-	W	S & Sply	threads	-	brown	-	as in TA/418, 419
TA/422	4067/8	-	W	Sply	threads	-	dark brown	-	as in TA/417, 418
TA/423	4067/9	L.10.0	W	Z	threads	-	dark red-brown	-	loose spun
TA/424	4091/3	L.c.30.0	S	Sply	threads	-	natural	-	loosely plied
TA/425	4094.3026	2.0 X 0.7	S	unspun	-	-	yellow*	-	mass silk reeled off cocoon onto narrow strip of wood used as spool; wood painted or dyed yellow
TA/426	4064.2945	(a) 15.0 X 2.5, 16.0 X c.2.5 15 X 6, 7.5 X 1.0 (b) 6.0 X 1.2 11 X 6, 5.5 X 3.5	W	-	felt	-	dark brown	-	stiff pieces, cut strips, and small scraps worn fragments, ?from hat brim
			W	-	felt	-	mid-brown	-	solid cut strip, ?new; softer than (a); other pieces worn; with scrap 14.0 X 1.0 worn leather
TA/427	3550	27.0 X 2.3, 2 mm thick	W	-	felt	-	dark brown, light brown	-	cut strips, very solidly made; similar strip, tied in knot.

Obj.no.	Excavat.no.	Measurement	Fibre	Spin	Weave	Count	Colour	Markers	Finishing	Sewing	Remarks
<u>?Probably 14th century</u>											
TA/428	101.2129	19.0 X 28.0	W	Z/S	2/1 twill	13/8	dark brown	-	-	-	warp fine even, weft uneven lumpy; 4 smaller fragments
<u>Unstratified</u>											
TA/429	X 4919/1	19.0 X 14.0	W+	Z/Z	2/2 twill	17/13	grey brown	3.1	-	x	edge, decorated parts 18 bobbles, ?sleeve or neck; 2 adjoining fragments, folded, corner right angle; selvage from seam? thread brown wool bobbles self-fabric, sewn brown wool (Pl. , p.
TA/430	X 4919/2	12.0 X 1.6	W	Z/S	tabby	11/12	dark brown	-	-	x	?collar, 2 adjoining pieces cut bias, curving to ?front; tiny fragments silk facing, selvage oversewn in seam, natural S silk; 6 bobbles & snumps, sewn silk (Pl. , p.
			S	Z/U	tabby	c.38/1	light brown	3.1	-	-	
TA/431	X 2706/1	5.0 X 8.5	W	Z/S	2/1 twill	14/9	dark brown, light brown	-	-	-	weft yarn variable, coarse, ?fe lts 2 threads thrown together, but sadder, ?narrow stripe
TA/432	X 2706/2	14.0 X 21.0	W	Z/S	tabby S extended tabby / 76	11/11	dark brown, light brown	-	-	-	stripe 2.8 wide over 2 warps, edge brown, narrow, light brown, dark brown, centre light brown 3-4 throws