## ANCIENT MONUMENTS LABORATORY

## REPORT

3988

SERIES/No	TECHNOLOGY		
AUTHOR	Paul Wilthew	30 June	1983
TITLE	Examination of S Wickford, Essex	Small <b>F</b> inds	from

## Examination of Small Finds from Wickford, Essex.

PAUL WILTHEW, ANCIENT MONUMENTS LABORATORY

The material examined (AM 830734-830736) included pigments, silver objects, lead and iron from Romano-British contexts. Qualitative elemental analysis of the samples was carried out by energy dispersive X-ray Fluorescence (XRF) and the compounds present in some samples were identified by X-ray diffraction (XRD). The analytical results and identifications of the objects, which are discussed below, are given in the appendix.

The appearance and elemental analysis of the pigment samples (AM 830734) suggested that they were probably all (except Cat. 1572) egyptian blue, a synthetic calcium copper silicate used as a pigment. This was confirmed for four of them by XRD, and the others were almost certainly the same. Cat. 1572 was probably a deposit of metallic lead in a sherd, rather than a pigment, which had oxidised on the surface to give a pale red appearance.

The deposits on the iron mail (AM 830735) were all types found fairly regularly on excavated iron objects, the blue material being vivianite, an iron phosphate corrosion product sometimes produced when iron objects corrode in waterlogged (reducing) conditions.

Of the possible silver objects (AM 830736, one (357 x 850, 131) was magnetic and was in fact iron, and the other three were silver, but the silver also contained some copper in each case. Various other elements were also detected on analysing the samples (see appendix) but of these iron is almost certainly only present because of surface contamination. The silver finger ring (L14A, 2, 8.8.67) originally consisted of two silver parts, the ring itself and a decorative, roughly hemispherical "button" soldered together by a lead-tin solder.

AM No.	Excavator's	Major elements detected by XRF	<u>Compounds</u> identified by XRD	Identification
830734 "" "" 830735 830736 ""	362 404 3458 4237 4591 4592 4593 C26A, 1968 Cat. 1572 Fe 279 Cat. 2258 L13A, 2, 1967 357 x 850, 131 325' 8 x 131' 4, 3 L14A, 2, 8.8. 67	$\frac{Cu}{Cu}$ , Fe, Ca, Pb, Sn $\frac{Cu}{Cu}$ , Fe, Ca, Pb Cu, Fe, Ca, Pb, Sn $\frac{Pb}{Pb}$ , Fe, Ca $\frac{Fe}{Fe}$ , Mn Ag, Cu, Pb, Fe, ?Au Fe Ag, Cu, Zn, Au, Pb, Fe Ring: Ag, Cu Solder: Ag, Cu, Pb, Sn	Ca Cu Si <sub>4</sub> $0_{10}$ Ca Cu Si <sub>4</sub> $0_{10}$ Ca Cu Si <sub>4</sub> $0_{10}$ Ca Cu Si <sub>4</sub> $0_{10}$ Ca Cu Si <sub>4</sub> $0_{10}$ Blue material: Fe <sub>3</sub> (PO <sub>4</sub> ) <sub>2</sub> . 8H <sub>2</sub> 0	Egyptian blue (pigment) "" "" "" Egyptian blue in sherd Lead in sherd Silver ring Iron fragments Silver pin Silver finger ring, with silver button lead-tin soldered on

Appendix - Analytical results and identifications of the samples