

4959

WOOD IDENTIFICATION OF SAMPLES FROM :-

PDU 51 - Pudding Lane 56 samples.
 MAN 32 - 21-29 Mansell St. 4 samples.
 LUD 32 - 42-46 Ludgate Hill. 1 sample.
 TUD 73 - 5 Tudor St. 1 sample.

Pudding Lane.

CON 3291 AN 1076. Roman writing tablet - probably Picea sp, spruce or Larix sp., larch. It is not possible to separate these genera on anatomical structures alone.

CON 2308 AN 1193. Roman. Cedrus sp, cedar, or Abies sp., silver fir; the condition of this sample prevents more positive identification.

CON 2308 AN 1197 Roman barrel - Cedrus sp or Abies sp.

CON 1874 AN 1279 Roman - Cedrus sp. or Abies sp.

CON 2308 AN 1194 Roman - Cedrus sp. or Abies sp.

CON 2308 AN 1203 Roman - Quercus sp., oak.

CON 3216 AN 1744 Roman writing tablet - Cedrus sp. or Abies sp.

CON 246 AN 59 Peg. - Family Salicaceae which includes Populus sp. poplar and Salix sp., willow. These genera can not be separated anatomically.

CON 3216 AN 1722 Roman Cedrus sp. or Abies sp.

CON 266 AN 234 Buxus sp., box.

CON 2308 AN 1192 Quercus sp.

CON 1348 AN 589 Roman barrel - Cedrus sp. or Abies sp.

CON 2308 AN 1204 Roman - Quercus sp.

CON 2308 AN 1195 Roman barrel - Cedrus sp. or Abies sp.

CON 2308 AN 1196 Roman barrel - Cedrus sp. or Abies sp.

CON 266 AN 60 Barrel - Quercus sp.

CON 1808 AN 706 Roman bobbin - Buxus sp., box.

CON 2308 AN 1202 Roman - Quercus sp.

CON 2065 AN 703 Wedge - Fraxinus sp., ash.

CON 1874 AN 1208 Roman - possibly Cedrus sp. or Abies sp. but the condition is too deteriorated to be certain.

CON 2308 AN 1199 Roman - Cedrus sp or Abies sp.

CON 2308 AN 1201 Roman - Quercus sp.

CON 2308 AN 1198 Roman barrel - Picea sp. or Larix sp.

CON 3077 AN 693 Bowl - Fagus sp., beech.

CON 203 AN 57 Post.Med. stopper. Sample very soft and decayed . It wasnot possible to obtain good sections howe ver the structure that was visible appeared to be composed of corky cells suggesting that this may have originated from the bark of the cork oak, Quercus suber.

pudding Lane cont.....2.

CON 3216 AN 698 Roman writing tablet - the structure is too decayed to identify this beyond a conifer, (softwood).
CON 3276 AN 1045 Roman bung - probably Abies sp. or Cedrus sp .
CON 3216 AN 1724 Roman - Abies sp. or Cedrus sp.
CON 1897 AN 1988 Barrel - probably Quercus sp. but condition is poor.
CON 3208 AN 1060 Roman - Cedrus sp. or Abies sp.
CON 3216 AN 1987 Roman waste 2 fragments - 1 frag. - Quercus sp.
1 frag. - Cedrus sp/Abies sp
CON 3216 AN 1725 Roman - Fagus sp., beech.
CON 3216 AN 1726 Roman barrel - Cedrus sp. or Abies sp.
CON 3216 AN 1984 Roman waste 5 fragments- 2 frag.- Picea sp/Larix sp
3 frag.- Cedrus sp/Abies sp.
CON 3216 AN 1717 Roman barrel - Cedrus sp. or Abies sp.
CON 3216 AN ? to accession and keep - 4 fragments - Cedrus sp or Abies sp
CON 3216 AN 1743 Roman waste 3 fragments - 7 frag. Quercus sp.
1 frag. Fagus sp.
CON 3216 AN 1725 Roman - Fagus sp.
CON 3077 AN 1077 Roman bung - Quercus sp.

21- 29 Mansell Street

CON 37 AN 297 Post med. - Pinus sp., pine.
CON 88 AN 296 Sample with nails - longest section -condition too poor to identify. wood around the nails at right-angles to longest section - conifer , possibly Pinus sp., pine.
CON 37 AN 298 Post med. Condition very poor , insufficient structure to identify.

42-46 Ludgate Hill.

CON 1080 AN 90 Med. decorative turned item. Buxus sp., box.

5 Tudor Street.

CON + AN 33. Dish - Fraxinus sp., ash.

Rowena Gale
28 July 1986