

ANCIENT MONUMENTS LABORATORY

Ref-# 1935

MATERIAL WOOD

SITE:.....ALDWINCIE A.S.Well..... (DATE: 29/9/75)

SHEET:1.....

AM No	X-Ray-No	Photo-No	Description and Report	Ref No
749066			Oak (<u>Quercus</u> sp.)	2
"			"	9
"			Possibly alder (<u>Alnus glutinosa</u> (L.) or hazel (<u>Corylus avellana</u> L.)	19
"			Very distorted. Possibly alder/hazel.	23
"			Alder/hazel. Possibly hazel.	24
"			Oak.	29
"			Oak.	34
"			Oak.	36
"	Upright posts (unnumbered)		16 oak. 1 possibly hawthorn-type (<u>Crataegus</u> / <u>Pyrus</u> / <u>Malus</u> / <u>Sorbus</u> sp) 1 probably alder.	
"	Wattle		About 50% of one bag was identified. The following species were present:- Ash (<u>Fraxinus excelsior</u> L.) ,twigs c10mm diam. Hazel, twigs c 5-15mm diam. Of blackthorn (<u>Prunus</u> sp.), twigs 5-20mm diam. Oak, a few fragments from fairly large timbers. Most fragments still had the bark present.	
	Wood from the large soil sample		About 50% was identified. It consisted almost entirely of branching twigs, often with the bark still on. The following species was identified:- Of blackthorn (<u>Prunus</u> sp.) Numerous twigs 5-40 mm diam.	

Carole A. Keepe