To take the place of No. 3954.

kaunds. Northants

(hevised note)

rextiles

prisabeth Crowfort

rib.es: neh.Appleyard, for al.

All the possible textile matter from the haunds excavation was combonised. reagments of two different of the could be recognised, in one part mixed with vegetable matter, ? grass or straw, other fibrous pieces may have been animal ?hair. A carbonised leather fragment could have come from part of a shoe or bag.

The fibre of the textiles could not be identified, but their appearance, with a very clear surface and Z-spinning, suggests flax. Both weaves are tably (plain weave), originally of good medium to fine quality, linen suitable for garments such as shirtd, women's caps or kerchiefs. The finer weave (textile 1, 3595.171, 6314.902) lies in closely pressed layers or folds, suggesting it may have been gathered or tied at one end. The one tiny fragment of a rather classer tably (Textile 2) lay on 962.

that dating of undecorated fragments is impossible; but these pieces are consistent with the 14th century date suggested for the destruction of the room. Anglish medieval flax spinning is always Z, and fragments of very similar quality and appearance to these have frequently been found in scrouds from medieval burials, wrapping coins or metal objects, and in town excavations, including sinchester, Morwich, and the City of London, from the 11th to 16th centuries.

catalogue

- 3995.171. Textite 1 varbonised fragments (a) two probably adjoining, (011625)

 6. A 4.3, 2.7 A 2.8 cm. Appearance suggests flax; spin Z both systems, weave tabby, count c.20-22/22-24 threads per cm; close-pressed layers or folds. (b) c.0.8 X 0.7 cm, count c. 12/13 on 5 mm; one weft? paired; fragment mixed with ?grass.

 11.4.Ap.leyerd (b) only structure visible flat and ribbon-like; in the thinner places it is possible to see spiral structures associated with grasses and straws. Possibly some type of grass or splinters of thin-walled straw.
- 6314.982. Textile 1 Carbonised lump, 2.5 x 2.0 cm, similar to above, (840267) again in folds; count c.1./12 on 5 mm.

 Textile 2 Adhering to 1, scrap 7 x 5 mm; ω/Z , tabby, c unt $\delta/6$ on 5 mm.
- 6271.1000. Lump carbonised ?leather, with marks from fine threads of a .8402667 weave, probably <u>rextile 1</u>.
- 6801.1088. Carbonised area 2.0 A 2.2 cm, 4.5 mm thick, fibrous surface, (821857) Pleather. One very coarse 2-spun thread caught in a fold, ? from bas or shoe.
- oacc.103y. Small fragment carbonised ?leather.

 Sarbonised fragments, best c.3.0 k l.5 cm, ?hair.

 h.M.Apployard: These fibres appear to be fused together, probable animal, but detail obscured by blackness and deposits.